

NFPA[®]

2112

Standard on
Flame-Resistant Clothing for
Protection of Industrial Personnel
Against Short-Duration Thermal
Exposures from Fire

2023



IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® STANDARDS

NFPA® codes, standards, recommended practices, and guides (“NFPA Standards”), of which the document contained herein is one, are developed through a consensus standards development process approved by the American National Standards Institute. This process brings together volunteers representing varied viewpoints and interests to achieve consensus on fire and other safety issues. While the NFPA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in NFPA Standards.

The NFPA disclaims liability for any personal injury, property, or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on NFPA Standards. The NFPA also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making NFPA Standards available, the NFPA is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is the NFPA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

The NFPA has no power, nor does it undertake, to police or enforce compliance with the contents of NFPA Standards. Nor does the NFPA list, certify, test, or inspect products, designs, or installations for compliance with this document. Any certification or other statement of compliance with the requirements of this document shall not be attributable to the NFPA and is solely the responsibility of the certifier or maker of the statement.



ALERT: THIS STANDARD HAS BEEN MODIFIED BY A TIA OR ERRATA

NFPA codes, standards, recommended practices, and guides (“NFPA Standards”) may be superseded at any time by the issuance of a new edition, be amended with the issuance of Tentative Interim Amendments (TIAs), or be corrected by Errata. This updating considers the then-current and available information on incidents, materials, technologies, innovations, and methods that develop over time. Therefore, any previous edition may no longer represent the current NFPA Standard on the subject matter. NFPA encourages the use of the most current edition of any NFPA Standard [as it may be amended by TIA(s) or Errata]. An official NFPA Standard at any point in time consists of the current edition of the document, with any issued TIAs and Errata. Visit the “Codes & Standards” section at www.nfpa.org for more information.

ADDITIONAL IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® STANDARDS

Updating of NFPA Standards

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Standards”) should be aware that these documents may be superseded at any time by the issuance of a new edition, may be amended with the issuance of Tentative Interim Amendments (TIAs), or be corrected by Errata. It is intended that through regular revisions and amendments, participants in the NFPA standards development process consider the then-current and available information on incidents, materials, technologies, innovations, and methods as these develop over time and that NFPA Standards reflect this consideration. Therefore, any previous edition of this document no longer represents the current NFPA Standard on the subject matter addressed. NFPA encourages the use of the most current edition of any NFPA Standard [as it may be amended by TIA(s) or Errata] to take advantage of current experience and understanding. An official NFPA Standard at any point in time consists of the current edition of the document, including any issued TIAs and Errata then in effect.

To determine whether an NFPA Standard has been amended through the issuance of TIAs or corrected by Errata, visit the “Codes & Standards” section at www.nfpa.org.

Interpretations of NFPA Standards

A statement, written or oral, that is not processed in accordance with Section 6 of the Regulations Governing the Development of NFPA Standards shall not be considered the official position of NFPA or any of its Committees and shall not be considered to be, nor be relied upon as, a Formal Interpretation.

Patents

The NFPA does not take any position with respect to the validity of any patent rights referenced in, related to, or asserted in connection with an NFPA Standard. The users of NFPA Standards bear the sole responsibility for determining the validity of any such patent rights, as well as the risk of infringement of such rights, and the NFPA disclaims liability for the infringement of any patent resulting from the use of or reliance on NFPA Standards.

NFPA adheres to the policy of the American National Standards Institute (ANSI) regarding the inclusion of patents in American National Standards (“the ANSI Patent Policy”), and hereby gives the following notice pursuant to that policy:

NOTICE: The user’s attention is called to the possibility that compliance with an NFPA Standard may require use of an invention covered by patent rights. NFPA takes no position as to the validity of any such patent rights or as to whether such patent rights constitute or include essential patent claims under the ANSI Patent Policy. If, in connection with the ANSI Patent Policy, a patent holder has filed a statement of willingness to grant licenses under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, copies of such filed statements can be obtained, on request, from NFPA. For further information, contact the NFPA at the address listed below.

Law and Regulations

Users of NFPA Standards should consult applicable federal, state, and local laws and regulations. NFPA does not, by the publication of its codes, standards, recommended practices, and guides, intend to urge action that is not in compliance with applicable laws, and these documents may not be construed as doing so.

Copyrights

NFPA Standards are copyrighted. They are made available for a wide variety of both public and private uses. These include both use, by reference, in laws and regulations, and use in private self-regulation, standardization, and the promotion of safe practices and methods. By making these documents available for use and adoption by public authorities and private users, the NFPA does not waive any rights in copyright to these documents.

Use of NFPA Standards for regulatory purposes should be accomplished through adoption by reference. The term “adoption by reference” means the citing of title, edition, and publishing information only. Any deletions, additions, and changes desired by the adopting authority should be noted separately in the adopting instrument. In order to assist NFPA in following the uses made of its documents, adopting authorities are requested to notify the NFPA (Attention: Secretary, Standards Council) in writing of such use. For technical assistance and questions concerning adoption of NFPA Standards, contact NFPA at the address below.

For Further Information

All questions or other communications relating to NFPA Standards and all requests for information on NFPA procedures governing its codes and standards development process, including information on the procedures for requesting Formal Interpretations, for proposing Tentative Interim Amendments, and for proposing revisions to NFPA standards during regular revision cycles, should be sent to NFPA headquarters, addressed to the attention of the Secretary, Standards Council, NFPA, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101; email: stds_admin@nfpa.org.

For more information about NFPA, visit the NFPA website at www.nfpa.org. All NFPA codes and standards can be viewed at no cost at www.nfpa.org/docinfo.

Copyright © 2022 National Fire Protection Association®. All Rights Reserved.

NFPA® 2112

Standard on

Flame-Resistant Clothing for Protection of Industrial Personnel Against Short-Duration Thermal Exposures from Fire

2023 Edition

This edition of NFPA 2112, *Standard on Flame-Resistant Clothing for Protection of Industrial Personnel Against Short-Duration Thermal Exposures from Fire*, was prepared by the Technical Committee on Flash Fire Protective Garments. It was issued by the Standards Council on June 16, 2022, with an effective date of July 6, 2022, and supersedes all previous editions.

This document has been amended by one or more Tentative Interim Amendments (TIAs) and/or Errata. See “Codes & Standards” at www.nfpa.org for more information.

This edition of NFPA 2112 was approved as an American National Standard on July 6, 2022.

Origin and Development of NFPA 2112

The NFPA Standards Council established the Technical Committee on Flash Fire Protective Garments in 1998. Between February and August of 1999, the technical committee developed two draft standards: NFPA 2112 and NFPA 2113, *Standard on Selection, Care, Use, and Maintenance of Flame-Resistant Garments for Protection of Industrial Personnel Against Flash Fire*, which were then released for public proposals and comments. NFPA 2112 specifies the minimum design, performance, certification requirements, and test methods for flame-resistant garments for use in areas at risk from flash fires. The first editions of NFPA 2112 and NFPA 2113 were approved by the NFPA membership at the May 2001 NFPA World Fire Safety Congress and were issued by the Standards Council in July 2001.

The 2007 edition revised the scope to clarify that the standard applies to the performance of fabrics and components of garments and not the garment itself. The scope was also modified to indicate that NFPA 2112 does not apply to single-use or limited-use garments. The committee pursued the development of separate documents to address the design, testing, certification, selection, and use of those garments. This revision also incorporated updates to reference test methods and the method for calculating total heat flux.

The 2012 edition updated the term *thermal protective performance* to *heat transfer performance* and incorporated ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame Resistant Materials for Clothing with Continuous Heating*, as the test method. The test method previously shown in the standard was removed, because it duplicated the ASTM F2700 method. A definition for *cold weather insulation material* and testing requirements were added to ensure that garments incorporating such insulation material are properly tested and certified. The 2012 edition clarified certain aspects of the laundering requirements to prevent the presence of residual detergent during testing.

For the 2018 edition, the technical committee refined the term *flash fire* to *short duration thermal exposure from fire*, which is a more descriptive term for the hazard that the standards address. Revisions were made to change the terms. The term *inherent flame resistance* also was added to the standard from NFPA 1971, *Standard on Protective Ensembles for Structural Fire Fighting and Proximity Fire Fighting*.

New garments were added to the standard, including shrouds/hoods/balaclavas as one item, and gloves. Shrouds/hoods/balaclavas were defined to cover those items intended to protect the head and/or neck. Gloves were defined as garments designed to protect the hands and wrist. The technical committee decided to include only performance and construction requirements for these garments without an ASTM F1930, *Standard Test Method for Evaluation of Flame Resistant Clothing for Protection Against Fire Simulations Using an Instrumented Manikin*, style test. These requirements

include, but are not limited to, construction, thermal shrinkage, heat transfer protective performance, flame resistance, thread, hardware, and interlinings.

TIA 12-2 was issued to address cold weather insulation and interlining for the 2012 edition. Prior to the issuance of the TIA, testing for afterflame, fire resistance, and thermal shrinkage had been performed on materials in a configuration not representative of that seen in application. Typically, these materials serve as internal insulation when used in garments in the field, and therefore not directly exposed to fire. However, during testing, the materials had been directly exposed to fire, which resulted in restricted use of cold weather gear without adding additional safety to the garments.

The TIA incorporated modifications to the testing requirements for cold weather and interlining materials for the 2012 edition to allow the use of these materials in NFPA 2112 gear. For the 2018 edition, the technical committee incorporated these allowances for the performance and testing requirements.

New requirements were added for emblems that are represented as flame resistant. Separate testing requirements were added to confirm that the fire-resistant emblems provide the desired performance. Reflective striping also now needs to be tested for flame resistance.

Finally, due to a concern about variability in the ASTM F1930 testing standard, the technical committee added two requirements to the testing apparatus to address variability. First, the lab must verify the response from the sensors to a heat flux before being mounted on the manikin. Second, the TC has added a requirement for two standard reference garments which are constructed of known materials with known results. Before a lab can certify results for the manikin test, the lab must test the reference garments and attain results within a predisposed range.

For the 2023 edition, the technical committee has added a new definition and requirements for venting material. Certification requirements have been added to the standard to properly document testing laboratories where fabric components are tested. Additionally, new annual recertification requirements have been added for samples of products compliant with this standard.

Test methods have been updated by the committee to include specific requirements for testing specimens from whole knitted gloves, as well as new requirements on the standard garment design and updated procedures for the manikin test.

TIA 18-1 was issued for the 2018 edition to address the COVID-19 pandemic and the need for industrial workers to wear cloth face coverings in the performance of their duties as dictated by federal, state, or local authorities. The inclusion of flame-resistant cloth face coverings was intended to aid in worker safety under the circumstances of the global pandemic in the personal protection against airborne pathogens. For the 2023 edition, the technical committee has incorporated these updates but changed the term “cloth face covering” to “barrier face covering” to align with the definition provided in ASTM F3502.

New requirements also have been added to ensure barrier face coverings are certified, labeled, and listed in the same manner as other clothing items covered in the standard.

Technical Committee on Flash Fire Protective Garments

Steven Addington, Chair
Eastman Chemical Company, TN [U]

Peter Clark, Apparel Solutions International Inc., Canada [M]
Rep. Alberta Burn Rehabilitation Society

James Douglas Dale, University of Alberta, Canada [RT]

Alec Feldman, Fulcrum Consultants, Ireland [SE]
Rep. JOIFF-International Organisation for Industrial Hazard Management

Brian W. Focht, PECO Energy, An Exelon Company, PA [U]

Diane B. Hess, PBI Performance Products, Inc., NC [M]

Darren D. Hewston, Freeport-McMoRan Oil & Gas, TX [U]

Tricia L. Hock, ASTM/Safety Equipment Institute (SEI), VA [RT]

Pamela A. Kavalesky, Intertek Testing Services, NY [RT]

Bob Kopko, R A K Welding And Industrial Sales, OH [U]

Joshua D. Moody, Milliken & Company/Westex, Inc., SC [M]

John Morton-Aslanis, North Carolina State University, NC [RT]

Amanda H. Newsom, UL LLC, NC [RT]

Eduardo Ramirez Bettoni, Xcel Energy, MN [U]

Paul Schiffelbein, Dupont Protection Solutions, VA [M]

Brian P. Shiels, ArcWear, KY [RT]

Joel E. Sipe, Exponent, Inc., CA [SE]

Denise N. Statham, Workwear Outfitters, TN [M]

Andrew Wirts, NASCO Industries, IN [M]

Alternates

Jason L. Allen, Intertek Testing Services, NY [RT]
(Alt. to Pamela A. Kavalesky)

James Cliver, Milliken & Company/Westex, Inc., SC [M]
(Alt. to Joshua D. Moody)

Francesco Colella, Exponent, Inc., MA [SE]
(Alt. to Joel E. Sipe)

Nicholas Galloway, UL LLC, NC [RT]
(Alt. to Amanda H. Newsom)

Caroline Holtzman, Dupont, VA [M]
(Alt. to Paul Schiffelbein)

Matthew Barker, NFPA Staff Liaison

Joshua Ingram, PBI Performance Products, NC [M]
(Alt. to Diane B. Hess)

Jill Kirby, ArcWear, KY [RT]
(Alt. to Brian P. Shiels)

Stephen Paskaluk, University of Alberta, Canada [RT]
(Alt. to James Douglas Dale)

Robert Simmonds, Safety Equipment Institute (SEI), NY [RT]
(Alt. to Tricia L. Hock)

This list represents the membership at the time the Committee was balloted on the final text of this edition. Since that time, changes in the membership may have occurred. A key to classifications is found at the back of the document.

NOTE: Membership on a committee shall not in and of itself constitute an endorsement of the Association or any document developed by the committee on which the member serves.

Committee Scope: This Committee shall have primary responsibility for documents on the manufacture, selection, care, and use of garments and equipment used for protection of industrial personnel where there is potential for flash fire. Industrial personnel include workers who are potentially or may accidentally be exposed to hydrocarbon or combustible dust flash fires, and not electrical flashes. These documents do not cover firefighters and other emergency services personnel.

Contents

Chapter 1 Administration	2112- 5	6.2 Use of a Liner for Cold Weather Insulation. . .	2112- 12
1.1 Scope.	2112- 5	6.3 Venting Materials.	2112- 12
1.2 Purpose.	2112- 5	6.4 Barrier Face Coverings.	2112- 12
1.3 Application.	2112- 5	Chapter 7 Performance Requirements	2112- 12
1.4 Retroactivity.	2112- 5	7.1 Garment and Fabric Requirements.	2112- 12
1.5 Equivalency.	2112- 5	7.2 Thread Requirements.	2112- 13
1.6 Units.	2112- 5	7.3 Hardware Requirement.	2112- 13
Chapter 2 Referenced Publications	2112- 6	7.4 Label Requirement.	2112- 13
2.1 General.	2112- 6	7.5 Shroud/Hood/Balaclava Requirements.	2112- 13
2.2 NFPA Publications.	2112- 6	7.6 Glove Requirements.	2112- 13
2.3 Other Publications.	2112- 6	7.7 Barrier Face Covering Requirements.	2112- 14
2.4 References for Extracts in Mandatory Sections.	2112- 6	Chapter 8 Test Methods	2112- 14
Chapter 3 Definitions	2112- 6	8.1 Sample Preparation Procedures.	2112- 14
3.1 General.	2112- 6	8.2 Heat Transfer Performance (HTP) Test.	2112- 14
3.2 NFPA Official Definitions.	2112- 6	8.3 Flame Resistance Test.	2112- 16
3.3 General Definitions.	2112- 7	8.4 Heat and Thermal Shrinkage Resistance Test.	2112- 17
Chapter 4 Certification	2112- 8	8.5 Manikin Test.	2112- 19
4.1 General.	2112- 8	8.6 Thread Heat Resistance Test.	2112- 21
4.2 Certification Program.	2112- 8	8.7 Label Print Durability Test.	2112- 21
4.3 Inspection and Testing.	2112- 9	8.8 Protective Glove Flame Resistance Test.	2112- 22
4.4 Manufacturer's Quality Assurance Program. . .	2112- 10	Annex A Explanatory Material	2112- 24
Chapter 5 Labeling and Information	2112- 11	Annex B Properties for Evaluating Flame- Resistant Garments, Shrouds/Hoods/ Balaclavas, and Gloves	2112- 27
5.1 Product Label Requirements.	2112- 11	Annex C Informational References	2112- 32
5.2 User Information.	2112- 12	Index	2112- 33
Chapter 6 Design Requirements	2112- 12		
6.1 Garments, Shrouds/Hoods/Balaclavas, Gloves, and Barrier Face Coverings.	2112- 12		

NFPA 2112

Standard on

Flame-Resistant Clothing for Protection of Industrial Personnel Against Short-Duration Thermal Exposures from Fire

2023 Edition

IMPORTANT NOTE: This NFPA document is made available for use subject to important notices and legal disclaimers. These notices and disclaimers appear in all publications containing this document and may be found under the heading “Important Notices and Disclaimers Concerning NFPA Standards.” They can also be viewed at www.nfpa.org/disclaimers or obtained on request from NFPA.

UPDATES, ALERTS, AND FUTURE EDITIONS: New editions of NFPA codes, standards, recommended practices, and guides (i.e., NFPA Standards) are released on scheduled revision cycles. This edition may be superseded by a later one, or it may be amended outside of its scheduled revision cycle through the issuance of Tentative Interim Amendments (TIAs). An official NFPA Standard at any point in time consists of the current edition of the document, together with all TIAs and Errata in effect. To verify that this document is the current edition or to determine if it has been amended by TIAs or Errata, please consult the National Fire Codes® Subscription Service or the “List of NFPA Codes & Standards” at www.nfpa.org/docinfo. In addition to TIAs and Errata, the document information pages also include the option to sign up for alerts for individual documents and to be involved in the development of the next edition.

NOTICE: An asterisk (*) following the number or letter designating a paragraph indicates that explanatory material on the paragraph can be found in Annex A.

A reference in brackets [] following a section or paragraph indicates material that has been extracted from another NFPA document. Extracted text may be edited for consistency and style and may include the revision of internal paragraph references and other references as appropriate. Requests for interpretations or revisions of extracted text shall be sent to the technical committee responsible for the source document.

Information on referenced and extracted publications can be found in Chapter 2 and Annex C.

Chapter 1 Administration

1.1 Scope. The standard shall specify the minimum design, performance, testing, and certification requirements and test methods for flame-resistant garments, shrouds/hoods/balaclavas, gloves, and barrier face coverings for use in areas at risk from short-duration thermal exposure from fire.

1.2 Purpose.

1.2.1* This standard shall provide minimum requirements for the design, construction, evaluation, and certification of flame-resistant garments, shrouds/hoods/balaclavas, gloves, and barrier face coverings for use by industrial personnel, with the

intent of not contributing to the burn injury of the wearer, providing a degree of protection to the wearer, and reducing the severity of burn injuries resulting during egress from or accidental exposure to short-duration thermal exposure from fire.

1.2.2* Controlled laboratory tests used to determine compliance with the performance requirements of this standard shall not be deemed as establishing performance levels for all situations to which personnel can be exposed.

1.2.3* This standard shall not be intended to be utilized as a detailed manufacturing or purchasing specification but shall be intended to be referenced in purchase specifications as minimum requirements.

1.3 Application.

1.3.1 This standard shall apply to the design, manufacturing, and certification of new flame-resistant garments, shrouds/hoods/balaclavas, and gloves and the design and manufacturing of new barrier face coverings.

1.3.2* This standard shall not apply to protective clothing for wildland firefighting, technical rescue, structural firefighting, proximity firefighting, or any other firefighting operations or hazardous materials emergencies. This standard shall not apply to single-use or limited-use garments. This standard shall not apply to protection from electrical flashes, radiological agents, biological agents, or hazardous materials.

1.3.3 Certification of flame-resistant garments to the requirements, shrouds/hoods/balaclavas, or gloves of this standard shall not preclude certification to additional appropriate standards where the garment, shrouds/hoods/balaclavas, or gloves meet all the applicable requirements of each standard.

1.3.4 The requirements of this standard shall not apply to accessories that might be attached to flame-resistant garments, shrouds/hoods/balaclavas, gloves, or barrier face coverings unless specifically addressed herein.

1.3.5 The minimum requirements identified in this standard are not intended to meet all the protection needs of a user in areas at risk from short-duration thermal exposure from fire. Users shall refer to NFPA 2113 for conducting the appropriate hazard assessment to identify the in-use area’s minimum protection requirements.

1.4 Retroactivity. This standard shall apply only to garments, shrouds/hoods/balaclavas, gloves, or barrier face coverings manufactured on or after the effective date of the standard.

1.5 Equivalency. Nothing herein shall restrict any jurisdiction or manufacturer from exceeding these minimum requirements.

1.6 Units. In this standard, values for measurement are followed by an equivalent in parentheses, but only the first stated value shall be regarded as the requirement. Equivalent values in parentheses shall not be considered as the requirement, as these values might be approximate.

Chapter 2 Referenced Publications

2.1 General. The documents or portions thereof listed in this chapter are referenced within this standard and shall be considered part of the requirements of this document.

2.2 NFPA Publications. National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 2113, *Standard on Selection, Care, Use, and Maintenance of Flame-Resistant Garments for Protection of Industrial Personnel Against Short-Duration Thermal Exposures from Fire*, 2020 edition.

2.3 Other Publications.

2.3.1 AATCC Publications. American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

AATCC TM158, *Dimensional Changes on Drycleaning, in Perchloroethylene: Machine*, 2016.

2.3.2 ASTM Publications. ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959.

ASTM D6413/D6413M, *Standard Test Method for Flame Resistance of Textiles (Vertical Test)*, 2015.

ASTM D7138, *Standard Test Method to Determine Melting Temperature of Synthetic Fibers*, 2016.

ASTM F1930, *Standard Test Method for Evaluation of Flame-Resistant Clothing for Protection Against Fire Simulations Using an Instrumented Manikin*, 2018.

ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame-Resistant Materials for Clothing with Continuous Heating*, 2008, reapproved 2020.

ASTM F2894, *Standard Test Method for Evaluation of Materials, Protective Clothing, and Equipment for Heat Resistance Using a Hot Air Circulating Oven*, 2019.

ASTM F3502, *Standard Specification for Barrier Face Coverings*, 2021.

2.3.3 ISO Publications. International Organization for Standardization, ISO Central Secretariat, BIBC II Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland.

ISO 9001, *Quality management systems — Requirements*, 2015.

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*, 2017.

ISO/IEC 17065, *Conformity assessment — Requirements for bodies certifying products, processes, and services*, 2012.

2.3.4 Other Publications.

Merriam-Webster's Collegiate Dictionary, 11th edition, Merriam-Webster, Inc., Springfield, MA, 2003.

2.4 References for Extracts in Mandatory Sections.

NFPA 270, *Standard Test Method for Measurement of Smoke Obscuration Using a Conical Radiant Source in a Single Closed Chamber*, 2018 edition.

NFPA 921, *Guide for Fire and Explosion Investigations*, 2021 edition.

NFPA 1971, *Standard on Protective Ensembles for Structural Fire Fighting and Proximity Fire Fighting*, 2018 edition.

NFPA 1977, *Standard on Protective Clothing and Equipment for Wildland Fire Fighting*, 2022 edition.

NFPA 1983, *Standard on Life Safety Rope and Equipment for Emergency Services*, 2017 edition.

NFPA 1991, *Standard on Vapor-Protective Ensembles for Hazardous Materials Emergencies and CBRN Terrorism Incidents*, 2016 edition.

Chapter 3 Definitions

3.1 General. The definitions contained in this chapter shall apply to the terms used in this standard. Where terms are not defined in this chapter or within another chapter, they shall be defined using their ordinarily accepted meanings within the context in which they are used. *Merriam-Webster's Collegiate Dictionary*, 11th edition, shall be the source for the ordinarily accepted meaning.

3.2 NFPA Official Definitions.

3.2.1* Approved. Acceptable to the authority having jurisdiction.

3.2.2* Authority Having Jurisdiction (AHJ). An organization, office, or individual responsible for enforcing the requirements of a code or standard, or for approving equipment, materials, an installation, or a procedure.

3.2.3 Labeled. Equipment or materials to which has been attached a label, symbol, or other identifying mark of an organization that is acceptable to the authority having jurisdiction and concerned with product evaluation, that maintains periodic inspection of production of labeled equipment or materials, and by whose labeling the manufacturer indicates compliance with appropriate standards or performance in a specified manner.

3.2.4* Listed. Equipment, materials, or services included in a list published by an organization that is acceptable to the authority having jurisdiction and concerned with evaluation of products or services, that maintains periodic inspection of production of listed equipment or materials or periodic evaluation of services, and whose listing states that either the equipment, material, or service meets appropriate designated standards or has been tested and found suitable for a specified purpose.

3.2.5 Shall. Indicates a mandatory requirement.

3.2.6 Should. Indicates a recommendation or that which is advised but not required.

3.2.7 Standard. An NFPA standard, the main text of which contains only mandatory provisions using the word “shall” to indicate requirements and that is in a form generally suitable for mandatory reference by another standard or code or for adoption into law. Nonmandatory provisions are not to be considered a part of the requirements of a standard and shall be located in an appendix, annex, footnote, informational note, or other means as permitted in the NFPA manuals of style. When used in a generic sense, such as in the phrases “standards development process” or “standards development activities,” the term “standards” includes all NFPA standards, including codes, standards, recommended practices, and guides.

3.3 General Definitions.

3.3.1 Accreditation/Accredited. A system whereby a certification organization determines that a laboratory has demonstrated the ability to conduct tests in an accurate and precise manner consistent with the requirements of this standard, accepts the laboratory's test data, and continues to monitor laboratory practices to ensure accurate and precise testing consistent with the requirements of this standard.

3.3.2 Agents.

3.3.2.1 Biological Agents. Biological materials that are capable of causing an acute disease or long-term damage to the human body. [1991, 2016]

3.3.2.2 Radiological Agents. Radiation associated with x-rays, alpha, beta, and gamma emissions from radioactive isotopes, or other materials in excess of normal background radiation levels.

3.3.3* Barrier Face Covering. A product worn on the face, specifically covering at least the wearer's nose and mouth, with the primary purpose of providing source control and a degree of particulate filtration to reduce the amount of inhaled particulate matter.

3.3.4 Body.

3.3.4.1 Lower Body. The area of the body below the waist including the legs but excluding the ankles and feet.

3.3.4.2 Upper Body. The area of body above the waist and extending to the shoulders, including the arms and wrists but excluding the hands.

3.3.5 Breakopen. When testing thermal protective materials, a material's response during thermal exposure evidenced by the formation of a hole through the test specimen that can result in passage of heat and/or flame.

3.3.6 Certification/Certified. A system whereby a certification organization determines that a manufacturer has demonstrated the ability to produce a product that complies with the requirements of this standard, authorizes the manufacturer to use a label on listed products that comply with the requirements of this standard, and establishes a follow-up program conducted by the certification organization as a check on the methods the manufacturer uses to determine continued compliance with the requirements of this standard. [1971, 2018]

3.3.7 Certification Organization. An independent, third-party organization that determines product compliance with the requirements of this standard with a labeling/listing/follow-up program. [1971, 2018]

3.3.8* Cold Weather Insulation Material. Fabric that consists of one or more nonseparable layers that is used for protection in a low-temperature environment.

3.3.9 Compliance/Compliant. Meeting or exceeding all applicable requirements of this standard. [1971, 2018]

3.3.10 Component(s). Any material, part, or subassembly used in the construction of the compliant product. [1971, 2018]

3.3.11 Drip. A flow of liquid that lacks sufficient quantity or pressure to form a continuous stream and runs or falls in drops.

3.3.12* Emblem(s). Shields, heraldry, or printing that designates a governmental entity or a specific organization; rank, title, position, or other professional status that is painted, screened, embroidered, sewn, glued, bonded, or otherwise attached in a permanent manner.

3.3.13* Fabric. The one or more layers of textile material(s) used in the primary construction of protective garments.

3.3.13.1 Textile Fabric. A planar structure consisting of yarns or fibers. [1977, 2022]

3.3.14* Fire. A rapid oxidation process, which is an exothermic chemical reaction, resulting in the evolution of light and heat in varying intensities. [921, 2021]

3.3.15* Flame Resistance. The property of a material whereby combustion is prevented, terminated, or inhibited following the application of a flaming or nonflaming source of ignition, with or without subsequent removal of the ignition source. Flame resistance can be an inherent property of a material, or it can be imparted by specific treatment. [1971, 2018] (*See 3.3.15.1, Inherent Flame Resistance.*)

3.3.15.1 Inherent Flame Resistance. Flame resistance that is derived from the essential characteristic of the fiber or polymer. [1971, 2018]

3.3.16 Flash Fire. A type of short-duration fire that spreads by means of a flame front rapidly through a diffuse fuel, such as dust, gas, or the vapors of an ignitable liquid, without the production of damaging pressure.

3.3.17 Follow-Up Program. The sampling, inspections, tests, or other measures conducted by the certification organization on a periodic basis to determine the continued compliance of labeled and listed products that are being produced by the manufacturer to the requirements of this standard. [1977, 2022]

3.3.18 Functional. The ability of an item to continue to be utilized for its intended purpose.

3.3.19 Garments. Clothing including, but not limited to, coveralls, trousers, shirts, and outerwear.

3.3.19.1 Limited-Use Garment. A garment whose service life is limited by the manufacturer to a specified number of wear cycles and does not meet the testing requirements of this standard.

3.3.19.2* Single-Use Garment. A garment that is designed to be used one time and then disposed of.

3.3.20 Glove. An item designed to provide protection to the wearer's hand and wrist.

3.3.21 Hardware. Nonfabric components of the protective garment including, but not limited to, those made of metal or plastic.

3.3.22 Hazardous Material. Any solid, liquid, gas, or mixture thereof that can potentially cause harm to the human body through respiration, ingestion, skin absorption, or contact.

3.3.23 Hazardous Materials Emergencies. Incidents involving the release or potential release of hazardous materials. [1971, 2018]

3.3.24 Industrial Personnel. Workers who might be at risk of burn injuries resulting during egress from or accidental exposure to short-duration thermal exposure from fire.

3.3.25* Interlining. Any textile that is incorporated into any garment as a layer between outer and inner layers that covers only a small portion of the overall garment.

3.3.26 Lining. Any material that is attached and used to cover or partially cover the inside surface of a flame-resistant garment.

3.3.27 Melt. A response to heat by a material resulting in evidence of flowing or dripping. [1983, 2017]

3.3.28 Model. The collective term used to identify a group of elements or items of the same basic design and components from a single manufacturer produced by the same manufacturing and quality assurance procedures that are covered by the same certification. [1971, 2018]

3.3.29* Product. The compliant flame-resistant garment, shrouds/hoods/balaclavas, or gloves.

3.3.30* Product Label. A label or marking affixed to a product by the manufacturer containing compliant statements, certification statements, manufacturer or model information, or similar dates. [1971, 2018]

3.3.31 Reflective Striping. Material added to the exterior of the garment to enhance nighttime or daytime visibility.

3.3.32 Reinforcement. An additional layer of a textile material applied to a specific area of the protective garment to make that portion of the protective garment more resistant to wear.

3.3.33 Sample. An amount of the material, product, or assembly to be tested that is representative of the item as a whole. [270, 2018]

3.3.34 Seam. Any permanent attachment of two or more protective garment fabrics in a line formed by joining the separate material pieces.

3.3.34.1 Sewn Seam. A series of stitches joining two or more separate plies of material(s) of planar structure, such as textiles.

3.3.35 Separate. A material response evidenced by splitting or delaminating. [1971, 2018]

3.3.36* Short-Duration Thermal Exposure from Fire. A period of egress from or accidental exposure to thermal events, including but not limited to, vapor cloud fires, jet flames, liquid fires (pool fires or running liquid fires), solids fires (fires of solid materials or dust fires), or warehouse fires.

3.3.37* Shroud/Hood/Balaclava. An item of clothing designed to provide protection to the wearer's head or neck, or both, less the face opening.

3.3.38 Specimen. The item that undergoes testing; in some cases, the specimen is also the sample. [1971, 2018]

3.3.39 Transfer Film. A type of emblem characterized as a thin nontextile polymeric material thermally bonded to the exterior surface of a garment, excluding reflective striping.

3.3.40 Trouser. A garment that is designed to provide minimum protection to the lower torso and legs, excluding the ankles and feet.

3.3.41 Venting Material. A fabric material used in a flame-resistant garment to aid in the transfer of air through the garment for the primary purpose of increasing the wearer's comfort.

Chapter 4 Certification

4.1 General.

4.1.1 All flame-resistant garments, shrouds/hoods/balaclavas, gloves, and barrier face coverings that are labeled as being compliant with this standard shall meet or exceed all applicable requirements specified in this standard and shall be certified.

4.1.2 All test data used to determine compliance of flame-resistant garments, shrouds/hoods/balaclavas, gloves, and barrier face coverings with this standard shall be provided by an accredited testing laboratory.

4.1.3 All flame-resistant garments, shrouds/hoods/balaclavas, gloves, and barrier face coverings shall be labeled and listed.

4.1.3.1 Fabric components that are tested in accordance with Section 8.5 shall be listed.

4.1.3.2* The location of the testing laboratory where testing of fabric components is conducted shall be included in the listing, including, at a minimum, the following information:

- (1) Accredited laboratory name, identification, or designation
- (2) Accredited laboratory address

4.1.4 All flame-resistant garments, shrouds/hoods/balaclavas, gloves, and barrier face coverings shall have a product label that meets the requirements of Section 5.1.

4.1.5* The certification organization's label, symbol, or identifying mark shall be attached to the product label, be part of the product label, or be immediately adjacent to the product label.

4.1.6 Manufacturers shall not claim compliance with a portion(s) or segment(s) of the requirements of this standard and shall not use the name or identification of this standard in any statements about their respective product(s) unless the product(s) is certified as compliant to this standard.

4.1.7 The certification organization shall not certify any flame-resistant garments, shrouds/hoods/balaclavas, or gloves to the 2018 edition of this standard on or after the issue date of this standard.

4.1.8 The certification organization shall not permit any manufacturer to label any flame-resistant garments, shrouds/hoods/balaclavas, or gloves as compliant with the 2018 edition of this standard on or after the issue date of this standard, plus 18 months.

4.2 Certification Program.

4.2.1* The certification organization shall not be owned or controlled by manufacturers or vendors of the product being certified.

4.2.2 The certification organization shall be primarily engaged in certification work and shall not have a monetary interest in the product's ultimate profitability.

4.2.3 The certification organization shall be accredited for personal protective equipment in accordance with ISO/IEC 17065, *Conformity assessment — Requirements for bodies certifying products, processes, and services*.

4.2.4 The certification organization shall refuse to certify products to this standard that do not comply with all applicable requirements of this standard.

4.2.5* The contractual provisions between the certification organization and the manufacturer shall specify that certification is contingent on compliance with all applicable requirements of this standard.

4.2.5.1 There shall be no conditional, temporary, or partial certifications.

4.2.5.2 Manufacturers shall not be authorized to use any label or reference to the certification organization on products that are not manufactured in compliance with all applicable requirements of this standard.

4.2.6 The certification organization shall have a program to accredit laboratories to perform the tests required by this standard.

4.2.6.1 The accredited laboratory shall conduct the required tests and maintain documentation of test results.

4.2.6.2 The accredited laboratory shall have laboratory facilities and equipment available for conducting required tests.

4.2.7 A program for calibration of all instruments shall be in place and operating procedures shall be in use to ensure proper control of all testing.

4.2.8 In the absence of an accredited laboratory, the certification organization shall be permitted to have its own laboratory facilities and equipment available for conducting required tests.

4.2.9* The certification organization shall require the manufacturer to establish and maintain a program of production inspection and testing that meets the requirements of Section 4.4.

4.2.9.1 The certification organization shall ensure that the audit assurance program provides continued product compliance with this standard.

4.2.9.2 The certification organization shall permit the manufacturer to be registered to ISO 9001, *Quality management systems — Requirements*, in lieu of meeting the requirements of Section 4.4.

4.2.10 The certification organization and the manufacturer shall evaluate any changes affecting the form, fit, or function of the certified product to determine its continued certification to this standard.

4.2.11* The certification organization shall have a follow-up inspection program of the manufacturing facilities of the certified product, with a minimum of one visit per 12-month period.

4.2.12 As part of the follow-up inspection program, the certification organization shall review the manufacturer's records and sample product to ensure the following:

(1) Garments, shrouds/hoods/balaclavas, and gloves conform to the requirements of this standard.

(2) The manufacturer has documentation that the fabric and components used in the garment, shroud/hood/balaclava, and glove were tested by an accredited laboratory and comply with this standard.

(3) A manufacturing quality assurance plan meeting the requirements of this standard is in place.

4.2.13 The certification organization shall also have a follow-up inspection program of the accredited testing laboratory(ies).

4.2.13.1 The certification organization shall conduct a minimum of one visit per 12-month period.

4.2.13.2 The certification organization shall review the accredited laboratory's records and facilities to ensure required documentation is maintained and to ensure conformance with testing requirements.

4.2.14 The certification organization shall have a program for investigating field reports alleging malperformance or failure of listed products.

4.2.15* The certification organization shall require the manufacturer to have a product recall system as part of the manufacturer's quality assurance program.

4.2.16 The certification organization's operating procedures shall provide a mechanism for the manufacturer to appeal decisions, which shall include the presentation of information from both sides of a controversy to a designated appeals panel.

4.2.17 The certification organization shall be in a position to use legal means to protect the integrity of its name and label, which shall be registered and legally defended.

4.3 Inspection and Testing.

4.3.1 For the certification of flame-resistant garments, shrouds/hoods/balaclavas, and gloves, the certification organization shall conduct inspections of the manufacturing facility and the accredited laboratory, as specified in 4.3.2 through 4.3.9.

4.3.2 All inspections, evaluations, conditioning, and testing for certification or for recertification shall be conducted by the certification organization or a facility accredited for inspections, evaluations, conditioning, and testing in accordance with all requirements pertaining to testing laboratories in ISO 17025, *General requirements for the competence of testing and calibration laboratories*.

4.3.3 All inspections, evaluations, conditioning, or testing conducted by a product manufacturer shall not be used in the certification or recertification process unless the facility for inspections, evaluations, conditioning, or testing has been accredited in accordance with all requirements pertaining to testing laboratories in ISO 17025, *General requirements for the competence of testing and calibration laboratories*.

4.3.4 Inspection by the certification organization shall include a review of all product labels to ensure that all required label attachment, compliance statements, certification statements, and other product information are as specified for the specific item in Section 5.1.

4.3.5 Inspection by the certification organization shall include a review of any graphic representations used on product labels, as permitted in 5.1.6 to ensure that the systems are consistent

with the worded statements, are readily understood, and clearly communicate the intended message.

4.3.6 Inspection by the certification organization shall include a review of the user information required by Section 5.2 to ensure that the information has been developed and is available.

4.3.7 Inspection by the certification organization for determining compliance with the design requirements specified in Chapter 6 shall be performed on whole or complete products.

4.3.8 Testing conducted by the accredited laboratory in accordance with the testing requirements of Chapter 8, for determining product compliance with the applicable requirements specified in Chapter 7, shall be performed on samples representative of materials and components used in the actual construction of the flame-resistant garment, shroud/hood/balaclava, and glove or sample materials cut from a representative product.

4.3.9 Recertification.

4.3.9.1 Any change in the design, construction, or material of a compliant product shall require new inspection and testing to verify compliance with all applicable requirements of this standard that the certification organization determines can be affected by such change.

4.3.9.1.1 Recertification shall be conducted before labeling the modified products as being compliant with this standard.

4.3.9.2 Samples of products compliant to this standard shall undergo recertification on an annual basis that includes the following:

- (1) Inspection and evaluation to all design requirements as required by this standard on all manufacturer models and components
- (2) Testing to all performance requirements as required by this standard on all manufacturer models and components with the following protocol:
 - (a) Where a test method incorporates testing both before and after laundering conditioning as specified in 8.1.3 and the test generates quantitative results, recertification testing shall be limited to the conditioning that yielded the worst-case test result during the initial certification for the model or component.
 - (b) Where a test method incorporates testing both before and after laundering conditioning as specified in 8.1.3 and the test generates nonquantitative results (e.g., pass/fail for melt or drip), recertification shall be limited to a single conditioning procedure in any given year and subsequent annual recertification testing shall cycle through the remaining conditioning procedures to ensure all required conditionings are included over time.
 - (c) Where a test method requires the testing of three specimens, a minimum of one specimen shall be tested.
 - (d) Where a test method requires the testing of more than three specimens, a minimum of two specimens shall be tested.
 - (e) Manikin testing as specified in 7.1.5 shall be performed on a minimum of one specimen within a 5-year period.

4.3.10 Product Modifications.

4.3.10.1 The certification organization shall not permit any modifications, pretreatment, conditioning, or other such special processes of the product or any product component prior to the product's submission for evaluation and testing by the accredited laboratory.

4.3.10.2 The accredited laboratory shall accept, from the manufacturer for evaluation and testing for certification, only product or product components that are the same in every respect to the actual final product or product component.

4.3.10.3 The accredited laboratory shall not permit the substitution, repair, or modification, other than as specifically permitted herein, of any product or any product component during testing.

4.4 Manufacturer's Quality Assurance Program.

4.4.1 General.

4.4.1.1 The manufacturer shall provide and maintain a quality assurance program that includes a documented inspection and product recall system.

4.4.1.2 The manufacturer shall have an inspection system to substantiate conformance to this standard.

4.4.1.3* The manufacturer shall be permitted to be registered to ISO 9001, *Quality management systems — Requirements*, in lieu of meeting the requirements of 4.4.2 through 4.4.8.

4.4.2 Instructions.

4.4.2.1 The manufacturer shall maintain written inspection and testing instructions.

4.4.2.2 The instructions shall prescribe inspection and test of materials, work in process, and completed articles.

4.4.2.3 Criteria for acceptance and rejection of materials, processes, and final product shall be part of the instructions.

4.4.3 Records.

4.4.3.1 The manufacturer shall maintain records of all "pass" and "fail" tests.

4.4.3.2 Records shall indicate the disposition of the failed materials or products.

4.4.4 Inspection System. The manufacturer's inspection system shall provide for procedures that assure the latest applicable drawings, specifications, and instructions are used for fabrication, inspection, and testing.

4.4.5 Calibration Program.

4.4.5.1 The manufacturer shall maintain, as part of the quality assurance program, a calibration program of all instruments used to ensure proper control of testing.

4.4.5.2 The calibration program shall be documented as to the date of calibration and performance verification.

4.4.6 Inspection Status. The manufacturer shall maintain a system for identifying the inspection status of component materials, work in process, and finished goods.

4.4.7 Nonconforming Materials.

4.4.7.1 The manufacturer shall establish and maintain a system for controlling nonconforming material, including procedures for the identification, segregation, and disposition of rejected material.

4.4.7.2 All nonconforming materials or products shall be identified to prevent use, shipment, and intermingling with conforming materials or products.

4.4.8 **Third-Party Audit.** The manufacturer's quality assurance program shall be audited by the third-party certification organization to determine that the program ensures continued product compliance with this standard.

Chapter 5 Labeling and Information

5.1 Product Label Requirements.

5.1.1* All flame-resistant clothing shall have a product label or labels permanently and conspicuously attached to each flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering.

5.1.2 At least one product label shall be conspicuously located inside each flame-resistant garment, shroud/hood/balaclava, and glove.

5.1.3 Multiple label pieces shall be permitted in order to carry all statements and information required to be on the product label.

5.1.4* The certification organization's label, symbol, or identifying mark shall be permanently attached to the product label or shall be part of the product label.

5.1.5 All worded portions of the required label or product label shall be printed in English. Supplementary languages, in addition to English, shall be permitted.

5.1.6 Symbols and other pictorial graphic representations shall be permitted to be used to supplement worded statements on the label or product label.

5.1.7 Graphic representations shall be consistent to clearly communicate the intended message.

5.1.8 The following statement shall be printed legibly on the product label in letters at least 2.5 mm (0.10 in.) high:

THIS CLOTHING ITEM MEETS THE REQUIREMENTS OF
NFPA 2112-2023.

5.1.9 The following information shall also be printed legibly on the product label for each flame-resistant garment, shroud/hood/balaclava, and glove in letters at least 1.6 mm (0.063 in.) high:

- (1) Model name, number, or design
- (2) Manufacturer's name, identification, or designation
- (3) Manufacturer's address
- (4) Country of manufacture
- (5) Manufacturer's garment identification number, lot number, or serial number
- (6) Size
- (7) Fiber content for each primary fabric layer including cold weather insulation materials but excluding interlinings and labels

- (8) The words "DO NOT REMOVE"
- (9) The words "NFPA 2113 REQUIRES UPPER AND LOWER BODY COVERAGE"

5.1.9.1* At a minimum, the following information shall also be printed legibly on the product label for each flame-resistant barrier face covering in letters at least 1.6 mm (0.063 in.) high:

- (1) Model name, number, or design
- (2) Manufacturer's name, identification, or designation
- (3) Manufacturer's garment identification number, lot number, or serial number
- (4) "DO NOT REMOVE"

5.1.10 The product label shall also include the international symbol for "Read user instructions before use," as shown in Figure 5.1.10.

5.1.11 The manufacturer shall be permitted to exclude the international symbol for "Read user instructions before use," as described in 5.1.10, when all of the information specified in 5.2.1 is provided on the product label or other labels adjacent to the product label.

5.1.12 Garments, shrouds/hoods/balaclavas, or gloves with multiple layers, including an outer layer and removable cold weather insulation material layer, shall specify the certified configuration and include a warning on the label stating that all layers must be properly secured and worn in accordance with the manufacturer's instructions.

5.1.13 For garments, shrouds/hoods/balaclavas, or gloves with multiple layers that include an outer layer and a removable cold weather insulation layer, a label shall be conspicuously attached to the removable insulation layer that states "DO NOT WEAR THIS LINER BY ITSELF. FOR COMPLIANCE WITH THE REQUIREMENTS OF NFPA 2112, THE COMPLETE CLOTHING ITEM MUST BE WORN. FOR COMPLIANCE INFORMATION, SEE THE PRODUCT LABEL ON THE OUTER CLOTHING ITEM."




FIGURE 5.1.10 "Read User Instructions Before Use" Symbol.

5.2 User Information.

5.2.1* The manufacturer shall provide with each clothing item, at a minimum, the following instructions and information:

- (1) Pre-use information
 - (a) Safety considerations
 - (b) Limitations of use
 - (c) Marking recommendations and restrictions
 - (d) Warranty information
- (2) Preparation for use
 - (a) Sizing/adjustment
 - (b) Recommended storage practices
- (3) Inspection frequency and details
- (4) Donning and doffing procedures
- (5) Proper use consistent with NFPA 2113
- (6) Maintenance and cleaning
 - (a) Cleaning instructions and precautions
 - (b) Maintenance criteria and methods of repair where applicable
- (7) Retirement and disposal criteria

5.2.2* Manufacturers shall provide a sizing chart that indicates the range of key wearer measurements that are accommodated by each specific size of garment, shroud/hood/balaclava, glove, or rainwear.

Chapter 6 Design Requirements

6.1 Garments, Shrouds/Hoods/Balaclavas, Gloves, and Barrier Face Coverings.

6.1.1 **Hardware Finishes.** All flame-resistant hardware finishes shall be free of rough spots, burrs, or sharp edges.

6.1.2 **Metal Components.** Any metallic closure systems or metal components shall not come in direct contact with the body.

6.1.3 **Slide Fastener Tape Requirements.** All slide fastener tape shall be made of an inherently flame-resistant fiber.

6.2 **Use of a Liner for Cold Weather Insulation.** Garments shall be permitted to include liners in their construction including cold weather insulation materials where the liner is either integral to the garment or removable.

6.2.1* Where garments incorporate a cold weather insulation material as part of a removable lining system, the garment shall be designed such that the removable liner consisting of the cold weather insulation material cannot be independently worn.

6.3 Venting Materials.

6.3.1 Venting materials used on flame-resistant garments shall be covered by fabric meeting the requirements of this standard.

6.3.1.1 Where used on flame-resistant garments and not covered by fabric, venting materials shall not exceed 465 cm² (72 in.²) over the entire flame-resistant garment.

6.4 **Barrier Face Coverings.** Barrier face coverings shall meet the requirements of ASTM F3502, *Standard Specification for Barrier Face Coverings*, with the exception of the labeling requirements in Section 10.

Chapter 7 Performance Requirements

7.1 Garment and Fabric Requirements.

7.1.1 Fabric utilized in the construction of flame-resistant garments shall be tested for heat transfer performance (HTP) as specified in Section 8.2 and shall have a “spaced” HTP rating of not less than 25 J/cm² (6.0 cal/cm²) and a “contact” HTP rating of not less than 12.6 J/cm² (3.0 cal/cm²).

7.1.1.1 Where the flame-resistant garment consists of multiple and separable layers intended to be worn separately, the outer layer and the inner layer or layers shall be separately tested.

7.1.1.2 Where the flame-resistant garment consists of multiple layers intended only to be worn together, only the outer layer shall be tested.

7.1.2 Fabric, and cold weather insulation materials utilized in the construction of flame-resistant garments shall be tested for flame resistance as specified in Section 8.3, have a char length of not more than 100 mm (4 in.) and an afterflame of not more than 2 seconds, and not melt and drip.

7.1.2.1* Emblems that are placed on the exterior of the garment and are represented as being flame resistant shall be tested for flame resistance as specified in Section 8.3, shall have an afterflame of not more than 2 seconds, and shall not melt and drip.

7.1.2.2 Reflective striping utilized in the construction of flame-resistant garments shall be tested for flame resistance as specified in Section 8.3, shall have an afterflame of not more than 2 seconds, and shall not melt and drip.

7.1.2.3 Reinforcements placed on the exterior of the garment shall be tested for flame resistance as specified in Section 8.3, have an afterflame of not more than 2 seconds, and not melt and drip.

7.1.2.4 Lining material utilized in the construction of the garment shall be tested for flame resistance as specified in Section 8.3, have an afterflame of not more than 2 seconds, and not melt and drip.

7.1.2.5 Venting material utilized in the construction of the garment shall be tested for flame resistance as specified in Section 8.3, have an afterflame of not more than 2 seconds, and not melt and drip.

7.1.3 Fabric utilized in the construction of flame-resistant garments, excluding manufacturers' labels, linings, interlinings, venting materials, and cold weather insulation materials, shall be individually tested for thermal shrinkage resistance as specified in Section 8.4, and shall not shrink more than 10 percent in any direction.

7.1.4 Fabric, linings, cold weather insulation materials, other textile materials, venting materials, reinforcements, and reflective striping, other than those items described in 7.1.4.2 and 7.1.4.3, used in the construction of flame-resistant garments shall be individually tested for heat resistance in their original form as specified in Section 8.4 and shall not melt and drip, separate, or ignite.

7.1.4.1 Where emblems on the exterior of the garment are represented as flame resistant, the emblems shall be tested for heat resistance as specified in Section 8.4, and shall not melt and drip, separate, or ignite.

7.1.4.2 Labels and emblems not being represented as flame resistant shall not be required to be tested for heat resistance.

7.1.4.3 Interlinings, collar stays, elastics, and hook and pile fasteners, when not in direct contact with the skin, shall not be required to be tested for heat resistance.

7.1.5 Specimen garments shall be tested for overall fire exposure as specified in Section 8.5 as a qualification test for the material; have an average predicted body burn of not more than 50 percent with no single burn being equal to or greater than 55 percent based on the total surface area covered by sensors, excluding hands and feet; and not exhibit breakopen greater than 2.5 cm (1.0 in.) in any direction.

7.1.5.1 Where the flame-resistant garment consists of multiple layers intended to be worn separately, each wearable layer shall be tested separately. Where each wearable layer has been separately tested, the wearable combinations of these layers is not required to be tested.

7.1.5.2* Where the flame-resistant garment consists of multiple layers intended only to be worn together, specimen garments consisting of the outer layer only shall be permitted to be tested.

7.2 Thread Requirements. Specimens of all sewing thread utilized in the construction of flame-resistant garments, excluding embroidery, shall be made of an inherently flame-resistant fiber, shall be tested for heat resistance as specified in Section 8.6, and shall not melt.

7.3* Hardware Requirement. Specimens of hardware used in the construction of flame-resistant clothing items, including but not limited to buttons, fasteners, and nonfabric-based closures, shall be individually tested for heat resistance in their original form as specified in Section 8.4; shall not melt and drip, separate, or ignite; and shall remain functional.

7.4 Label Requirement. Specimen labels used in the construction of flame-resistant garments, shrouds/hoods/balaclavas, and gloves shall be tested, as specified in Section 8.7, for printing durability and shall remain legible and in place.

7.4.1 Specimen labels used in the construction of flame-resistant barrier face coverings shall be exempt from the requirements of Section 7.4.

7.5 Shroud/Hood/Balaclava Requirements.

7.5.1 Fabric utilized in the construction of flame-resistant shrouds/hoods/balaclavas shall be tested for heat transfer protective performance (HTP) as specified in Section 8.2, and shall have a "spaced" HTP rating of not less than 25 J/cm² (6.0 cal/cm²) and a "contact" HTP rating of not less than 12.6 J/cm² (3.0 cal/cm²).

7.5.2 Fabric utilized in the construction of flame-resistant shrouds/hoods/balaclavas shall be tested for flame resistance as specified in Section 8.3, and shall have a char length of not more than 100 mm (4 in.) and an afterflame of not more than 2 seconds, and shall not melt and drip.

7.5.3 Fabric utilized in the construction of flame-resistant shrouds/hoods/balaclavas, excluding manufacturers' labels, shall be individually tested for thermal shrinkage resistance as specified in Section 8.4, and shall not shrink more than 10 percent in any direction.

7.5.4 Fabric and other textile materials other than those items described in 7.1.4.2 and 7.1.4.3 used in the construction of flame-resistant shrouds/hoods/balaclavas shall be individually tested for heat resistance in their original form as specified in Section 8.4, and shall not melt and drip, separate, or ignite.

7.5.4.1 Labels and emblems shall not be required to be tested for heat resistance.

7.5.4.2 Interlinings, elastics, closures, and hook and pile fasteners, when not in direct contact with the skin, shall not be required to be tested for heat resistance.

7.5.5 Sewing thread utilized in the construction of flame-resistant shrouds/hoods/balaclavas, excluding embroidery, shall be made of an inherently flame-resistant fiber. Specimens of this thread shall be tested for heat resistance as specified in Section 8.6, and shall not melt.

7.5.6 Specimens of hardware used in the construction of flame-resistant shrouds/hoods/balaclavas, including but not limited to buttons, fasteners, and closures, shall be individually tested for heat resistance in their original form as specified in Section 8.4; shall not melt and drip, separate, or ignite; and shall remain functional.

7.5.7 Specimen labels used in the construction of flame-resistant shrouds/hoods/balaclavas shall be tested for printing durability as specified in Section 8.7 and shall remain legible.

7.6 Glove Requirements.

7.6.1 Gloves composites cut and sewn from flat materials shall be tested for heat transfer protective performance (HTP) as specified in Section 8.2 and have a "spaced" HTP rating of not less than 25 J/cm² (6.0 cal/cm²) and a "contact" HTP rating of not less than 12.6 J/cm² (3.0 cal/cm²).

7.6.2 Glove composites shall be tested for flame resistance as specified in Section 8.8 and as follows:

- (1) Have a char length of not more than 100 mm (4 in.)
- (2) Have an average afterflame of not more than 2 seconds
- (3) Not melt and drip
- (4) Not exceed 5.0 percent of the specimen's original weight in consumed material

7.6.2.1 Exterior, nonmetallic hardware used in the construction of flame-resistant gloves, excluding fasteners and zippers, shall be tested for flame resistance as specified in Section 8.8 and as follows:

- (1) Have an average afterflame of not more than 2 seconds
- (2) Not melt and drip

7.6.2.2 Trim; reinforcement materials; and external labels, tags, or emblems that are greater than 25.8 cm² (4 in.²) shall be included in these requirements.

7.6.2.3 Hook and loop fasteners, where not in direct contact with the skin, shall be excluded from these requirements.

7.6.3 Gloves shall be tested for thermal shrinkage resistance as specified in Section 8.4, and shall not have an average percent shrinkage of more than 10 percent in either direction.

7.6.4 Gloves shall be tested for heat resistance as specified in Section 8.4 and as follows:

- (1) Not melt and drip, separate, or ignite
- (2) Have all hardware remain functional

7.6.4.1 Trim; reinforcement materials; and external labels, tags, or emblems that are greater than 25.8 cm² (4 in.²) shall be included in these requirements. Separation shall not be evaluated.

7.6.4.2 Internal liners, elastics, internal labels, and hook and loop fasteners, where not in direct contact with the skin, shall be excluded from these requirements.

7.6.4.3 Internal liners, elastics, internal labels, and hook and loop fasteners, where in direct contact with the skin, shall not melt and drip, or ignite.

7.6.5 Sewing thread utilized in the construction of flame-resistant gloves, excluding embroidery, shall be made of an inherently flame-resistant fiber.

7.6.5.1 Specimens of this thread shall be tested for heat resistance as specified in Section 8.6, and shall not melt.

7.6.6 Specimen labels used in the construction of flame-resistant gloves shall be tested for printing durability as specified in Section 8.7 and shall remain legible.

7.7 Barrier Face Covering Requirements.

7.7.1 Fabric components used in the construction of barrier face coverings shall be compliant with all fabric requirements in Section 7.1.

7.7.2 Sewing thread components used in the construction of barrier face coverings shall be compliant with the thread requirements in Section 7.2.

7.7.3 Hardware components used in the construction of barrier face coverings shall be compliant with the hardware requirements in Section 7.3.

Chapter 8 Test Methods

8.1 Sample Preparation Procedures.

8.1.1 Application.

8.1.1.1 The sample preparation procedures contained in Section 8.1 shall apply to each test method in Chapter 8, as specifically referenced in the sample preparation section of each test method.

8.1.1.2 Only the specific sample preparation procedure or procedures referenced in the sample preparation section of each test method shall be applied to that test method.

8.1.2 Room Temperature Conditioning Procedure.

8.1.2.1 Specimens shall be conditioned at a temperature of 21°C ± 3°C (70°F ± 5°F) and a relative humidity of 65 percent ± 5 percent for at least 4 hours.

8.1.2.2 Specimens shall be tested within 5 minutes of removal from conditioning.

8.1.3* Washing and Drying Procedure. Where required, specimens shall be subjected to the specified number of cycles of washing and drying in accordance with the following procedure:

- (1) Each washing procedure shall be as specified in Table 8.1.3.

- (2)* When testing in accordance with 8.3.3.1, the final two cycles shall be run without adding any detergent or chemicals.
- (3) No bleach or softener shall be used during any portion of the laundry cycle.
- (4) The machine shall be filled with water to the specified level prior to adding chemicals.
- (5) The water level shall be determined by measuring inside the washing machine from the bottommost portion of the basket to the water surface.
- (6) The water level measurement shall be 12.7 cm (5.0 in.) for the low setting and 25.4 cm (10 in.) for the high setting.
- (7) Water hardness shall not exceed 25 ppm.
- (8) The extraction cycle shall continue as specified in Table 8.1.3 or until water is no longer flowing to the drain.
- (9) The load shall be removed immediately after the extraction cycle concludes.
- (10) A full load of 9 kg (20 lb) shall be laundered.
- (11) Fabric samples for washing shall be at least 1 m² (1 yd²) of each material.
- (12) Garments shall be permitted for conditioning.
- (13) A dummy load, if needed to make a full load, shall be of similar material as the test material.
- (14) The machine type shall be a front-loading industrial washer capable of performing the operations specified in Table 8.1.3 with the following dimensions:
 - (a) A drum diameter of 760 mm ± 50 mm (30 in ± 2 in.)
 - (b) A drum depth of 380 mm ± 50 mm (15 in ± 2 in.)
- (15) Sample specimens shall be tumble dried.
- (16) The dryer temperature shall be preset to provide a dryer exhaust temperature of 68°C ± 3°C (155°F ± 5°F) without a load.
- (17) Wash water temperature shall be within ±3°C (±5°F) of the value in Table 8.1.3.

8.1.3.1 In Table 8.1.3, carryover shall be accomplished with agitation.

8.1.4 Dry Cleaning Procedure.

8.1.4.1 Where required, specimens shall be subjected to the required number of cycles of dry cleaning in accordance with the procedures of Sections 9.2 and 9.3 of AATCC TM158, *Dimensional Changes on Drycleaning, Perchloromethylene: Machine*.

8.1.4.2 Fabric samples for dry cleaning shall be at least 1 m² (1 yd²) of each material.

8.1.4.3 Garments shall be permitted for conditioning.

8.2 Heat Transfer Performance (HTP) Test.

8.2.1 Application. This test method shall apply to flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering fabrics.

8.2.1.1 Modifications to this test method for testing specimens from whole knitted gloves shall be as specified in 8.2.8.

8.2.2 Specimens.

8.2.2.1 HTP testing shall be conducted on six specimens — three in the spaced configuration and three in the contact configuration — measuring 150 mm ± 5 mm × 150 mm ± 5 mm (6 in. ± ¼ in. × 6 in. ± ¼ in.) and shall consist of all layers repre-

Table 8.1.3 Washing Cycle Procedure

Operations	Time (min)	Temperature		Water Level	Quantity per Wash Load	
		°C	°F		g	oz
Break	10	66	150	Low	—	—
Sodium metasilicate (or equivalent)	—	—	—	—	17	0.6
Sodium tripolyphosphate	—	—	—	—	11	0.4
Tergitol 15.S.9 or equivalent	—	—	—	—	22	0.8
Drain	1	—	—	—	—	—
Carryover*	5	66	150	Low	—	—
Drain	1	—	—	—	—	—
Rinse	2	57	135	High	—	—
Drain	1	—	—	—	—	—
Rinse	2	48	118	High	—	—
Drain	1	—	—	—	—	—
Rinse	2	38	100	High	—	—
Drain	1	—	—	—	—	—
Sour	5	38	100	Low	—	—
Sodium silicofluoride	—	—	—	—	6	0.2
Drain	1	—	—	—	—	—
Extract	5	—	—	—	—	—

*See 8.1.3.1.

sentative of the garment, shroud/hood/balaclava, glove, and barrier face covering to be tested.

8.2.2.2 Specimens shall consist of all layers used in the construction of the flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering excluding any areas with special reinforcements.

8.2.2.3 Specimens shall not include seams.

8.2.2.4 Specimens shall not be stitched to hold individual layers together.

8.2.3 Sample Preparation.

8.2.3.1 For fabrics that are designated on the flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering labels to be washed, specimens shall be tested before and after three cycles of washing and drying as specified in 8.1.3.

8.2.3.2 For fabrics that are designated on the flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering labels to be dry-cleaned, specimens shall be tested before and after three cycles of dry cleaning as specified in 8.1.4.

8.2.3.3 For fabrics that are designated on the flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering labels to be either washed or dry-cleaned, specimens shall be tested before and after three cycles of washing and drying as specified in 8.1.3, or after three cycles of dry cleaning as specified in 8.1.4.

8.2.4 Apparatus. The test apparatus shall be that specified in ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame-Resistant Materials for Clothing with Continuous Heating*.

8.2.5 Procedure.

8.2.5.1 Heat transfer performance testing shall be performed in accordance with ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame-Resistant Materials for Clothing with Continuous Heating*.

8.2.5.2 Single layer specimen heat transfer performance testing shall use the Relaxed Single Layer configuration in ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame-Resistant Materials for Clothing with Continuous Heating*, for testing in spaced and contact orientation.

8.2.5.3 Multilayer specimen HTP testing shall use the Multiple Layer Samples configuration in ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame-Resistant Materials for Clothing with Continuous Heating*, for testing in spaced and contact orientation.

8.2.6 Report.

8.2.6.1 The individual test HTP rating of each specimen shall be reported separately for both “spaced” and “contact” tests.

8.2.6.2 The individual average HTP ratings for both “spaced” and “contact” tests shall also be reported.

8.2.6.3 If an HTP rating is greater than 60, then the HTP rating shall be reported as “>60.”

8.2.7 Interpretation.

8.2.7.1 Pass or fail determinations shall be separately based on the individual average HTP ratings for both “spaced” and “contact” tests.

8.2.7.2 If an individual result from any test set varies more than ± 10 percent from the average result, the results from the

test set shall be discarded and another set of specimens shall be tested.

8.2.8 Specific Requirements for Testing Specimens from Whole Knitted Gloves.

8.2.8.1 The specimen holder assembly specified in Section 6.9 of ASTM F2700, *Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame-Resistant Materials for Clothing with Continuous Heating*, shall be modified such that the size of the 100 mm × 100 mm (4 in. × 4 in.) square hole is reduced to a 75 mm × 75 mm (3 in. × 3 in.) or 50 mm × 50 mm (2 in. × 2 in.) square hole.

8.2.8.2 HTP testing shall be conducted on six specimens — three in the spaced configuration and three in the contact configuration — measuring 100 mm ± 5 mm × 100 mm ± 5 mm (4 in. ± ¼ in. × 4 in. ± ¼ in.) and consist of all layers representative of the whole knitted glove being tested.

8.2.8.3 Testing shall be performed as described in 8.2.2.2 through 8.2.7.

8.3 Flame Resistance Test.

8.3.1 Application.

8.3.1.1 This test method shall apply to each flame-resistant garment, shroud/hood/balaclava, and barrier face covering fabric layer.

8.3.1.2 Modifications to this test method for testing woven textile materials shall be as specified in 8.3.8.

8.3.1.3 Modifications to this test method for testing knit textile materials shall be as specified in 8.3.9.

8.3.1.4 Modifications to this test method for testing nonwoven, coated, or laminated textile materials shall be as specified in 8.3.10.

8.3.1.5 Modifications to this test method for testing small specimens and emblems, other than transfer film, shall be as specified in 8.3.11.

8.3.1.6 Modifications to this test method for testing reflective striping shall be as specified in 8.3.12.

8.3.1.7 Modifications to this test method for testing cold weather insulation materials shall be as specified in 8.3.13.

8.3.1.8 Modifications to this test method for testing transfer films shall be as specified in 8.3.14.

8.3.2 Specimens.

8.3.2.1 Each specimen shall consist of a 76 mm × 305 mm (3 in. × 12 in.) rectangle with the long dimension parallel to either the warp or filling, the wale or course, or machine or cross-machine direction of the material.

8.3.2.2 Each individual layer of multilayer material systems or composites shall be separately tested.

8.3.3 Sample Preparation.

8.3.3.1 For fabrics, cold weather insulation materials, shroud/hood/balaclava, and barrier face covering materials that are designated on the product label to be washed, specimens shall be tested before and after 100 cycles of washing and drying as specified in 8.1.3.

8.3.3.2 For fabrics, cold weather insulation materials, shroud/hood/balaclava, and barrier face covering materials that are designated on the product label to be dry-cleaned, specimens shall be tested before and after 100 cycles of dry cleaning as specified in 8.1.4.

8.3.3.3 For fabrics, cold weather insulation materials, shroud/hood/balaclava, and barrier face covering materials that are designated on the product label to be either washed or dry-cleaned, specimens shall be tested before and after 100 cycles of washing and drying as specified in 8.1.3, or before and after 100 cycles of dry cleaning as specified in 8.1.4.

8.3.4 **Apparatus.** The test apparatus shall be that specified in ASTM D6413/D6413M, *Standard Test Method for Flame Resistance of Textiles (Vertical Test)*.

8.3.5 Procedure.

8.3.5.1 Flame resistance testing shall be performed in accordance with ASTM D6413/D6413M, *Standard Test Method for Flame Resistance of Textiles (Vertical Test)*.

8.3.5.2 Each specimen shall be examined for evidence of melting and dripping.

8.3.6 Report.

8.3.6.1 Afterflame time and char length shall be reported for each specimen.

8.3.6.2 The average afterflame time and char length for each material shall be calculated and reported.

8.3.6.3 The afterflame time shall be reported to the nearest 0.2 second, and the char length to the nearest 3.2 mm (¼ in.).

8.3.6.4 Observations of melting and dripping for each specimen shall be reported.

8.3.7 Interpretation.

8.3.7.1 Pass/fail performance shall be based on any observed melting and dripping, the average afterflame time, and average char length.

8.3.7.2 Failure in either direction shall constitute failure of the material.

8.3.8 Specific Requirements for Testing Woven Textile Materials.

8.3.8.1 Five specimens from each of the warp and filling directions shall be tested.

8.3.8.2 No two warp specimens shall contain the same warp yarns, and no two filling specimens shall contain the same filling yarns.

8.3.8.3 Testing shall be performed as described in 8.3.2 through 8.3.7.

8.3.9 Specific Requirements for Testing Knit Textile Materials.

8.3.9.1 Five specimens from each of the two directions shall be tested.

8.3.9.2 Samples for conditioning shall include material that is a minimum of 76 mm × 305 mm (3 in. × 12 in.).

8.3.9.3 Testing shall be performed as described in 8.3.2 through 8.3.7.

8.3.10 Specific Requirements for Testing Nonwoven, Coated, or Laminated Textile Materials.

8.3.10.1 Five specimens from each of the machine and cross-machine directions shall be tested.

8.3.10.2 Testing shall be performed as described in 8.3.2 through 8.3.7.

8.3.11 Specific Requirements for Testing Small Materials and Emblems Other Than Transfer Films.

8.3.11.1* Five specimens attached to the textile layer as used in the protective garment shall be tested.

8.3.11.1.1 For the purpose of this testing, the textile layer shall be permitted to be of navy 200 g/m² (6.0 oz/yd²), nominal 100 percent aramid material.

8.3.11.1.2 When tested, emblems shall be attached to the textile layer in the same manner as normally used for attaching emblems to garment fabric.

8.3.11.2 The specimens shall be attached to the textile layer such that the bottom, exposure, edge of the item coincides with the bottom (exposure) edge of the textile support layer.

8.3.11.3 Testing shall be performed as described in 8.3.2 through 8.3.7, except char length shall not be measured.

8.3.12 Specific Requirements for Testing Reflective Striping.

8.3.12.1 Five reflective striping specimens for flammability testing shall be prepared by attaching the reflective striping to 76 mm × 305 mm (3 in. × 12 in.) pieces of fabric utilized in the construction of the garment, in the manner that it is normally attached to the fabric.

8.3.12.2 The reflective striping shall be oriented parallel to the long axis and in the center of the fabric.

8.3.12.3 Testing shall be performed as described in 8.3.2 through 8.3.7, except char length shall not be measured.

8.3.13 Specific Requirements for Testing Cold Weather Insulation Materials.

8.3.13.1 Samples for wash or dry-clean conditioning shall be prepared by cutting a 75 cm × 75 cm (30 in. × 30 in.) panel of the cold weather insulation material. A similar-sized piece of 200 g/m² to 270 g/m² (6.0 oz/yd² to 8.0 oz/yd²) flame-resistant fabric meeting all requirements of this standard shall be sewn around the perimeter of the cold weather insulation material such that the batting side is covered by the fabric.

8.3.13.2 Following wash or dry-clean conditioning, five specimens measuring 75 mm × 300 mm (3 in. × 12 in.) from each of the warp and filling directions shall be removed from the cold weather insulation material layer of the conditioned panels.

8.3.13.3 If applicable, all specimens shall be prepared for testing by trimming the scrim material, batting, or other layer(s) away from the face cloth by 50 mm ± 3 mm (2.0 in. ± 1/8 in.) such that the face cloth can be folded back covering the scrim, batting, or other layer(s) by 50 mm ± 3 mm (2.0 in. ± 1/8 in.); the folded specimen shall be secured in the specimen holder.

8.3.13.4 Testing shall be performed as described in 8.3.2 through 8.3.7.

8.3.14 Specific Requirements for Testing Transfer Films.

8.3.14.1 Transfer films shall be applied to individual specimens of the textile layer as used in the protective garment.

8.3.14.2 Five specimens from each of the warp and filling directions of the textile layer shall be tested.

8.3.14.3 Each specimen shall consist of a 76 mm × 305 mm (3 in. × 12 in.) rectangle with the long dimension parallel to the warp or filling direction of the material. The transfer film shall be placed in the center of the specimen with a minimum width of 25 mm (1 in.) and a minimum length of 305 mm (12 in.), oriented with respect to the textile short and long dimension, respectively, employing the same technique that is normally used in applying the transfer film on garment fabrics. Multiple adjacent transfer films shall be permitted to be utilized to achieve the minimum required area.

8.3.14.4 Testing shall be performed as described in 8.3.2 through 8.3.7.

8.3.14.5 Char length shall not be measured.

8.4 Heat and Thermal Shrinkage Resistance Test.**8.4.1 Application.**

8.4.1.1 This test method shall apply to flame-resistant garment, shroud/hood/balaclava, glove, and barrier face covering components, hardware, and cold weather insulation materials.

8.4.1.2 Modifications to this test method for testing flame-resistant garment textile materials shall be as specified in 8.4.8.

8.4.1.3 Modifications to this test method for testing other flame-resistant garment materials, including reflective striping, shall be as specified in 8.4.9.

8.4.1.4 Modifications to this test method for testing hardware shall be as specified in 8.4.10.

8.4.1.5 Modifications to this test method for testing cold weather insulation materials shall be as specified in 8.4.11.

8.4.1.6 Modifications to this test method for testing gloves shall be as specified in 8.4.12.

8.4.1.7 Modifications to this test method for testing emblems, including transfer films, shall be as specified in 8.4.13.

8.4.2 Specimens.

8.4.2.1 Only heat resistance testing shall be conducted on at least three specimens for each hardware item, shroud/hood/balaclava, cold weather insulation material, and other flame-resistant garment material not listed in 8.4.2.2 and 8.4.2.3.

8.4.2.2 Both heat and thermal shrinkage resistance testing shall be conducted on a minimum of three specimens for each flame-resistant garment, shroud/hood/balaclava, and barrier face covering fabric.

8.4.2.3 Each separable layer of multilayer material systems or composites shall be tested as an individual layer.

8.4.3 Sample Preparation.

8.4.3.1 For fabrics, cold weather insulation materials, shroud/hood/balaclava materials, and barrier face covering fabrics that are designated on the product label to be washed, specimens

shall be tested before and after three cycles of washing and drying as specified in 8.1.3.

8.4.3.2 For fabrics, cold weather insulation materials, shroud/hood/balaclava materials, and barrier face covering fabrics that are designated on the product label to be dry cleaned, specimens shall be tested before and after three cycles of dry cleaning as specified in 8.1.4.

8.4.3.3 For fabrics, cold weather insulation materials, shroud/hood/balaclava materials, and barrier face covering fabrics that are designated on the product label to be either washed or dry cleaned, specimens shall be tested before and after three cycles of washing and drying as specified in 8.1.3, or before and after three cycles of dry cleaning as specified in 8.1.4.

8.4.4 Apparatus.

8.4.4.1 The test oven shall be a horizontal flow circulating oven with minimum interior dimensions to permit the specimens to be suspended and be not less than 51 mm (2 in.) from any interior oven surface or other test specimens.

8.4.4.2 The test oven shall be as specified in ASTM F2894, *Standard Test Method for Evaluation of Materials, Protective Clothing, and Equipment for Heat Resistance Using a Hot Air Circulating Oven*.

8.4.5 Procedure.

8.4.5.1 The test procedure shall be as specified in ASTM F2894, *Standard Test Method for Evaluation of Materials, Protective Clothing, and Equipment for Heat Resistance Using a Hot Air Circulating Oven*, with the following modifications stated in 8.4.5.1.1 and 8.4.5.1.2.

8.4.5.1.1 The oven door shall not remain open more than 15 seconds.

8.4.5.1.2 The optional stretching frame shall be used for all knit specimens, where specified by the manufacturer.

8.4.6 Report.

8.4.6.1 Observations of ignition, melting and dripping, or separation shall be reported for each specimen.

8.4.6.2 The percent change in the width and length dimensions of each specimen shall be calculated, and the results shall be reported as the average of all three specimens in each dimension.

8.4.7 Interpretation.

8.4.7.1 Any evidence of ignition, melting and dripping, or separation on any specimen shall constitute failing performance.

8.4.7.2 The average percent change in both dimensions shall be used to determine pass/fail performance.

8.4.7.3 Failure in any one dimension shall constitute failure for the entire sample.

8.4.8 Specific Requirements for Testing Flame-Resistant Garments and Shroud/Hood/Balaclava Textile Materials.

8.4.8.1 Each specimen shall be 381 mm \pm 13 mm \times 381 mm \pm 13 mm (15 in. \pm 0.5 in. \times 15 in. \pm 0.5 in.), with 250 mm \pm 6 mm \times 250 mm \pm 6 mm (10 in. \pm 0.25 in. \times 10 in. \pm 0.25 in.) benchmarks, and shall be cut from the fabric to be utilized in the construction of the clothing item.

8.4.8.2 Testing shall be performed in accordance with 8.4.2 through 8.4.7.

8.4.9 Specific Requirements for Testing Other Flame-Resistant Garments, Shroud/Hood/Balaclava, Barrier Face Coverings, and Materials (Including Reflective Striping).

8.4.9.1 Specimen length shall be 152 mm (6 in.), except for textiles utilized in the clothing item in lengths less than 152 mm (6 in.), where lengths shall be the same as utilized in the clothing item.

8.4.9.2 Specimen width shall be 152 mm (6 in.), except for textiles or reflective striping utilized in the clothing item in widths less than 152 mm (6 in.), where widths shall be the same as utilized in the clothing item.

8.4.9.3 Samples for conditioning shall include material sewn onto a 0.84 m² (1 yd²) of 100 percent aramid material [navy dyed at 200 g/m² (6.0 oz/yd²)] no closer than 51 mm (2 in.) apart in parallel strips.

8.4.9.3.1 Specimens, except reflective striping, shall be removed from the ballast material prior to testing.

8.4.9.3.2 Specimens shall be placed in the oven with the long dimension of the specimen parallel to the oven sides.

8.4.9.3.3 Reflective striping specimens shall be placed in the oven with the striping parallel to the oven sides.

8.4.9.4 Testing shall be performed in accordance with 8.4.2 through 8.4.7, and thermal shrinkage shall not be measured.

8.4.10 Specific Requirements for Testing Hardware.

8.4.10.1 A minimum of three complete hardware items shall be tested.

8.4.10.2 Hardware shall not be conditioned.

8.4.10.3 Observations of hardware condition following heat exposure shall be limited to ignition.

8.4.10.4 Hardware shall be evaluated for functionality within 10 minutes following removal from the oven.

8.4.10.5 Testing shall be performed in accordance with 8.4.2 through 8.4.7, and thermal shrinkage shall not be measured.

8.4.11 Specific Requirements for Testing Cold Weather Insulation Materials.

8.4.11.1 Samples for wash or dry-clean conditioning shall be prepared by cutting a 50 cm \times 20 cm (20 in. \times 8 in.) panel of the cold weather insulation material. A similar-sized cloth piece of 200 g/m² to 270 g/m² (6.0 oz/yd² to 8.0 oz/yd²) flame-resistant fabric meeting all requirements of this standard shall be sewn around the perimeter of the cold weather insulation material such that the batting side is covered by the fabric.

8.4.11.2 Following wash or dry-clean conditioning, three specimens measuring 152 mm \times 152 mm (6 in. \times 6 in.) shall be removed from the cold weather insulation material layer of the conditioned panel.

8.4.11.3 Testing shall be performed in accordance with 8.4.2 through 8.4.7, and thermal shrinkage shall not be measured.

8.4.12 Specific Requirements for Testing Gloves.

8.4.12.1 Specimens shall include complete gloves.

8.4.12.2 Three glove specimens shall be tested.

8.4.12.3 Glove specimens shall be of a size such that they fit the following dimensions:

- (1) Hand length: 19.25 cm – 20.25 cm (7.58 in. – 7.97 in.)
- (2) Hand circumference: 19.25 cm – 23.25 cm (7.58 in. – 9.15 in.)

8.4.12.4 Specimen gloves shall be conditioned as specified in 8.1.2 prior to testing.

8.4.12.5 The dimensions of the glove specimen shall then be measured.

8.4.12.5.1 The length measurement of the glove specimen shall be from the tip of the middle finger to the end of the glove body on the palm side.

8.4.12.5.2 The width measurement of the glove specimen shall be the width measurement of the palm side 25 mm (1 in.) below the base of the fingers.

8.4.12.6 The glove body shall then be filled with 4 mm ($\frac{3}{16}$ in.) perforated soda-lime glass beads, with care taken to tightly pack the glass beads into the fingers of the glove and into the glove body.

8.4.12.6.1 A total of 75 mL \pm 5 mL (2.5 fl oz \pm 0.2 fl oz) of beads shall be proportionately distributed into the fingers.

8.4.12.6.2 A mesh bag shall be filled with 375 mL (12.7 fl oz) of beads.

8.4.12.6.3 The bag shall be closed to keep the beads from spilling out.

8.4.12.6.4 The mesh bag filled with beads shall be placed inside the body of the glove.

8.4.12.6.5 The glass beads shall be at a temperature of 21°C \pm 3°C (71°F \pm 5°F).

8.4.12.7 The opening of the glove shall be clamped together, and the specimen shall be suspended by the clamp in the oven so that the entire glove is not less than 50 mm (2 in.) from any oven surface or other specimen, and airflow is parallel to the plane of the glove.

8.4.12.8 The test oven shall be heated and the test thermometer stabilized at 260°C, 6/–0°C (500°F, 10/–0°F) for a minimum of 30 seconds.

8.4.12.9 After 5 minutes, 15/–0 seconds, of oven exposure at 260°C, 6/–0°C (500°F, 10/–0°F), the sample glove shall be removed and allowed to cool for a minimum of 2 minutes.

8.4.12.10 The specimen shall be examined for evidence of melting and dripping, separation, or ignition.

8.4.12.11 Hardware shall be evaluated for functionality within 10 minutes following removal from the oven.

8.4.12.12 After the oven exposure, the dimensions of the glove specimen shall also be measured as described in 8.4.12.5 to determine pass/fail.

8.4.12.13 The percentage of change in the width and length dimensions of the specimen shall be calculated. Results shall be reported as the average of all three specimens in each direction.

8.4.12.14 Testing shall be performed as described in 8.4.2 through 8.4.8.

8.4.13 Specific Requirements for Testing Emblems, Including Transfer Films.

8.4.13.1 Specimens shall consist of emblems or transfer films placed on 0.84 m² (1 yd²) of nominal 100 percent aramid material [navy 200 g/m² (6.0 oz/yd²)] fabric pieces that measure 152 mm \pm 6 mm \times 152 mm \pm 6 mm (65 in. \pm 0.25 in. \times 6 in. \pm 0.25 in.).

8.4.13.2 Representative emblems or transfer films specimens shall measure a minimum of 100 mm (4.0 in.) and 25 mm (1.0 in.) and shall be attached to individual fabric pieces in the same manner as normally applied for their attachment to garments. Multiple adjacent transfer films shall be permitted to be utilized to achieve the minimum required area.

8.4.13.3 Specimens shall be placed in the oven with the long dimension of the specimen parallel to the oven sides.

8.4.13.4 Testing shall be performed in accordance with 8.4.2 through 8.4.7, and thermal shrinkage shall not be measured.

8.5 Manikin Test.

8.5.1 Application. The manikin test shall apply to flame-resistant garment fabrics.

8.5.2 Specimens.

8.5.2.1 Three specimens shall be tested.

8.5.2.2 Fabrics to be tested shall be used to construct the standard garment design specified in 8.2.2 of ASTM F1930, *Standard Test Method for Evaluation of Flame-Resistant Clothing for Protection Against Fire Simulations Using an Instrumented Manikin*.

8.5.2.2.1 The standard garment design shall meet the following requirements before pre-conditioning:

- (1) The coverall shall have a convertible collar having a width of 70 mm \pm 6.4 mm (2.75 in. \pm 0.25 in.) when measured at the center back and collar points no longer than 70 mm \pm 6.4 mm (2.75 in. \pm 0.25 in.).
- (2) The full length of the metal slide fastener shall be exposed on the exterior of the garment.
- (3) The slide fastener tape shall be made with inherently flame-resistant fiber.
- (4) The garment shall be constructed without visibility markings or pockets, elastic, or other hardware such as snaps.
- (5) The sleeve end shall consist of a hemmed edge only with no banded cuff.
- (6) The coverall shall not have a waistband.
- (7) There shall be no elastic or strap-type closures for tightening in the waist area.
- (8) The sleeve opening shall be 27 cm \pm 2.5 cm (10.6 in. \pm 1 in.).
- (9) The leg opening shall be 42.5 cm \pm 3.8 cm (16.75 in. \pm 1.5 in.).

8.5.3 Sample Preparation.

8.5.3.1 For garments that are designated on the flame-resistant garment label to be washed, specimens shall be tested after one cycle of washing and drying as specified in 8.1.3.

8.5.3.2 For garments that are designated on the flame-resistant garment label to be dry-cleaned, specimens shall be tested after one cycle of dry cleaning as specified in 8.1.4.

8.5.3.3 For garments that are designated on the flame-resistant garment label to be either washed or dry-cleaned, specimens shall be tested after one cycle of washing and drying as specified in 8.1.3, or after one cycle of dry cleaning as specified in 8.1.4.

8.5.3.4 Samples for conditioning shall be full garments.

8.5.4 Standard Reference Garments. When tested in accordance with 8.5.4, results for 4.5 osy garments shall fall within range of 30 percent to 42 percent predicted body burn, and results for 6 osy garments shall fall within range of 16 percent to 24 percent predicted body burn to test garments for compliance to this standard.

8.5.4.1 Standard reference garments made from both 4.5 osy and 6 osy 93 percent dyeable, low crystallinity meta aramid/5 percent para aramid/2 percent inductive antistatic fiber shall be tested at a frequency of six months or less in accordance with 8.5.4.

8.5.4.1.1 The 4.5 osy reference garments shall be plain woven 4.5 osy/-0.2 osy 93 percent dyeable, low crystallinity meta aramid/5 percent para aramid/2 percent inductive antistatic fiber piece dyed royal blue with no finish. Fabric used to make garments shall be made from 38/2 /-5 percent cotton count yarn and have construction of 66 ends /-2 ends x 42 picks/-2 picks.

8.5.4.1.2 The 6.0 osy reference garments shall be plain woven 6.0 osy /-0.3 osy 93 percent dyeable, low crystallinity meta aramid/5 percent para aramid/2 percent inductive antistatic fiber piece dyed royal blue with no finish. Fabric used to make garments shall be made from 30/2 /-5 percent cotton count yarn and have construction of 67 ends /-2 ends x 46 picks/-2 picks.

8.5.4.1.3 The manikin shall be dressed in accordance with 8.5.6.2.

8.5.4.2 The laboratory shall maintain consistent test methodology for specimen garment testing and for both standard reference garments.

8.5.5 Apparatus.

8.5.5.1 Verify the system response annually, at a minimum, by performing the In-situ absorbed radiant energy testing specified in Section 10.3 of ASTM F1930, *Standard Test Method for Evaluation of Flame-Resistant Clothing for Protection Against Fire Simulations Using an Instrumented Manikin*, with the following specifications. If it is not possible to expose the sensor on the manikin itself with a handheld radiant heat source, an extension wire can be used to extend the wiring from the manikin to a bench-top radiant heat source.

- (1) A minimum of one sensor from each data acquisition card shall be tested.
- (2) A radiant heating source shall be used to conduct verification.
- (3) Exposures levels of 4000, 8000, and 12,000 W/m² (±5 percent) shall be used as verified with the appropriate NIST (or equivalent) traceable reference heat flux sensor.
- (4) The following tables shall be used to verify the system is predicting burns within the ranges specified:
 - (a) Table 8.5.5.1(a) shall be used for the 4000 W/m² (±5 percent) exposure.

- (b) Table 8.5.5.1(b) shall be used for the 8000 W/m² (±5 percent) exposure.
- (c) Table 8.5.5.1(c) shall be used for the 12,000 W/m² (±5 percent) exposure.

8.5.6 Procedure.

8.5.6.1 Specimens shall be tested in accordance with ASTM F1930, *Standard Test Method for Evaluation of Flame-Resistant Clothing for Protection Against Fire Simulations Using an Instrumented Manikin*, with the following specifications:

- (1) All testing, including calibrations, shall be conducted with a 3.0-second (±0.1) exposure.
- (2) The average incident heat flux shall be 84 kW/m² (2.0 cal/cm²-sec) (±5 percent), as follows:
 - (a) Heat flux data from one second to three seconds shall be used to calculate the incident heat flux.
 - (b) A numerical curve-fitting function shall not be used solely to calculate from the average value of all the sensors to determine the incident heat flux.

Table 8.5.5.1(a) Table of Acceptable Heat Flux Exposures and Allowable Time to Second-degree Burn Predictions

Exposure (W/m ²)	Predicted Time to Second-degree Burn(s)	Acceptable Range for Time to Second-degree Burn(s)
3800	39.3	35.4—43.2
3850	38.6	34.7—42.5
3900	38.0	34.2—41.8
3950	37.3	33.6—41.0
4000	36.7	33.0—40.4
4050	36.1	32.5—39.7
4100	35.6	32.0—39.2
4150	35.0	31.5—38.5
4200	34.5	31.1—38.0

Table 8.5.5.1(b) Table of Acceptable Heat Flux Exposures and Allowable Time to Second-degree Burn Predictions

Exposure (W/m ²)	Predicted Time to Second-degree Burn(s)	Acceptable Range for Time to Second-degree Burn(s)
7600	15.8	14.2—17.4
7650	15.6	14.0—17.2
7700	15.5	14.0—17.1
7750	15.4	13.9—16.9
7800	15.2	13.7—16.7
7850	15.1	13.6—16.6
7900	15.0	13.5—16.5
7950	14.8	13.3—16.3
8000	14.7	13.2—16.2
8050	14.6	13.1—16.1
8100	14.5	13.1—16.0
8150	14.4	13.0—15.8
8200	14.2	12.8—15.6
8250	14.1	12.7—15.5
8300	14.0	12.6—15.4
8350	13.9	12.5—15.3
8400	13.8	12.4—15.2

(3) Verify that the system response is sufficient such that the average incident heat flux is greater than or equal to 79 kW/m² (1.9 cal/cm²·sec) during a nude calibration exposure at the 1-second mark.

8.5.6.2 The manikin shall be dressed in 170 g/m² (5.0 oz/yd²) (\pm 10 percent), jersey knit, 100 percent cotton underwear briefs and 155 g/m² (4.6 oz/yd²) (\pm 10 percent) jersey knit, 100 percent cotton short-sleeve crew-neck T-shirts before the garment specimen is placed on it.

8.5.6.3 Procedure.

8.5.6.3.1 Upon completion of 8.5.6 and before removal of the test garment from the manikin, the test garment shall be visually inspected for breakopen.

8.5.6.3.2 Physical contact with the garment during visual inspection shall not occur except as permitted in 8.5.6.3.3.1.

8.5.6.3.3* The maximum length in the horizontal and vertical directions shall be measured in areas where breakopen has occurred.

8.5.6.3.3.1* Physical contact shall be permitted for taking measurements in accordance with 8.5.6.3.3.

8.5.7 Report.

8.5.7.1 The predicted percent body burn based on the total surface area covered by sensors, excluding hands and feet, for each specimen shall be reported.

8.5.7.2 The average predicted body burn of all specimens shall be calculated and reported.

8.5.7.3 Breakopen.

8.5.7.3.1 The number of areas where breakopen has occurred shall be recorded and reported for each specimen.

8.5.7.3.2 The maximum length shall be reported for each area of breakopen.

8.5.8 Interpretation. The average predicted body burn and the breakopen inspection shall be used to determine pass/fail performance for garment fabrics.

8.6 Thread Heat Resistance Test.

8.6.1 Application. The thread heat resistance test method shall apply to each type of thread used in the construction of the flame-resistant garment, shroud/hood/balaclava, gloves, and barrier face coverings other than embroidery.

8.6.2 Specimens. A total of three different determinations shall be made.

8.6.3 Sample Preparation.

8.6.3.1 Specimens shall be tested after conditioning as specified in 8.1.2.

8.6.3.2 Samples for conditioning shall be at least 10 cm (4 in.) long.

8.6.4 Procedure. Specimens shall be tested to a temperature of 260°C (500°F) in accordance with ASTM D7138, *Standard Test Method to Determine Melting Temperature of Synthetic Fibers*.

8.6.5 Report. The pass/fail results for each specimen tested shall be reported.

8.6.6 Interpretation. One or more thread specimens failing this test shall constitute failing performance for the thread type.

8.7 Label Print Durability Test.

8.7.1 Application. This test method shall apply to flame-resistant garment, shroud/hood/balaclava, and glove product labels.

8.7.2 Modifications to this test method for testing glove labels shall be as specified in 8.7.7.

8.7.3 Specimens. A total of three different specimen labels shall be evaluated.

8.7.4 Sample Preparation.

8.7.4.1 For fabrics, cold weather insulation materials, and shroud/hood/balaclava materials that are designated on the product label to be washed, specimens shall be tested before and after 100 cycles of washing and drying as specified in 8.1.3.

8.7.4.2 For fabrics, cold weather insulation materials, and shroud/hood/balaclava materials that are designated on the product label to be dry-cleaned, specimens shall be tested before and after 100 cycles of dry cleaning as specified in 8.1.4.

8.7.4.3 For fabrics, cold weather insulation materials, and shroud/hood/balaclava materials that are designated on the product label to be either washed or dry-cleaned, specimens shall be tested before and after 100 cycles of washing and drying as specified in 8.1.3, or before and after 100 cycles of dry cleaning as specified in 8.1.4.

8.7.4.4 Samples for conditioning by laundering or dry cleaning shall include labels sewn onto a square sample of fabric measuring 0.84 m² (1 yd²), meeting the requirements of Section 7.1. The labels shall be no closer than 51 mm (2 in.) apart in parallel strips.

8.7.5 Procedure. Specimens shall be examined for legibility at a distance of 30.5 cm (12 in.) by the unaided eye with 20/20 vision, or vision corrected to 20/20, for legibility to determine pass/fail.

Table 8.5.5.1(c) Table of Acceptable Heat Flux Exposures and Allowable Time to Second-degree Burn Predictions

Exposure (W/m ²)	Predicted Time to Second-degree Burn(s)	Acceptable Range for Time to Second-degree Burn(s)
11,400	9.1	8.2—10.0
11,500	9.0	8.1—9.9
11,600	8.8	7.9—9.7
11,700	8.7	7.8—9.6
11,800	8.6	7.7—9.5
11,900	8.5	7.7—9.4
12,000	8.4	7.6—9.2
12,100	8.3	7.5—9.1
12,200	8.2	7.4—9.0
12,300	8.2	7.4—9.0
12,400	8.1	7.3—8.9
12,500	8.0	7.2—8.8
12,600	7.8	7.0—8.6

8.7.6 Report. The pass/fail results for each specimen tested shall be reported.

8.7.7 Interpretation. One or more label specimens failing this test shall constitute a failing performance.

8.7.8 Specific Requirements for Testing Glove Labels.

8.7.8.1 For gloves that are designated on the flame-resistant glove label to be either washed or dry-cleaned, specimens shall be tested before and after three cycles of washing and drying as specified in 8.1.3, or after three cycles of dry cleaning as specified in 8.1.4.

8.7.8.2 Specimens shall include complete gloves with labels attached.

8.8 Protective Glove Flame Resistance Test.

8.8.1 Application.

8.8.1.1 This test method shall be applied to glove materials.

8.8.1.2 Modifications to this test method for testing small materials shall be as specified in 8.8.8.

8.8.2 Specimens.

8.8.2.1 Each specimen to be tested shall be a rectangle at least 50 mm (2 in.) wide by 150 mm (6 in.) long.

8.8.2.2 Specimens shall be the composite used in actual glove construction consisting of each single layer, with all layers arranged in proper order.

8.8.2.2.1 Three specimens shall be tested for each composite.

8.8.2.2.2 If a proposed glove construction has stitched-through seams, three additional specimens containing these seams shall be tested. The seam shall be in the direction of the 150 mm (6 in.) dimension.

8.8.2.3 In each test, the specimen's normal outer surface shall be exposed to the flame.

8.8.3 Sample Preparation.

8.8.3.1 Specimens shall be tested after conditioning as specified in 8.1.2.

8.8.3.2 Additional specimens shall be tested after three cycles of washing and drying as specified in 8.1.3, or after three cycles of dry cleaning as specified in 8.1.4, followed by conditioning as specified in 8.1.2.

8.8.4 Apparatus.

8.8.4.1 The test apparatus shall consist of a burner, crucible tongs, support stand, utility clamp, stopwatch, butane gas, gas regulator valve system, and measuring scale.

8.8.4.1.1 The burner shall be a high-temperature, liquefied-type Fisher burner.

8.8.4.1.2 The stopwatch or other timing device shall measure the burning time to the nearest 0.1 second.

8.8.4.1.3 The butane shall be commercial grade, 99.0 percent pure or better.

8.8.4.1.4 The gas regulator system shall consist of a control valve system with a delivery rate designed to furnish gas to the burner under a pressure of $17.3 \text{ kPa} \pm 1.7 \text{ kPa}$ ($2.5 \text{ psi} \pm 0.25 \text{ psi}$) at the reducing valve. The flame height shall be

adjusted at the reducing valve to produce a pressure of $0.7 \text{ kPa} \pm 0.07 \text{ kPa}$ ($0.1 \text{ psi} \pm 0.01 \text{ psi}$).

8.8.4.2 A freestanding flame height indicator shall be used to assist in adjustment of the burner flame height. The indicator shall mark a flame height of 75 mm (3 in.) above the top of the burner.

8.8.4.3 A specimen support assembly shall be used that consists of a frame and steel rod of 2 mm ($\frac{1}{16}$ in.) diameter to support the specimen in an L-shaped position, as shown in Figure 8.8.4.3.

8.8.4.4 When mounted in the apparatus, the specimen measurements shall be not less than 50 mm (2 in.) for the horizontal portion and not less than 100 mm (4 in.) for the vertical portion.

8.8.4.5 The specimen shall be held at each end by spring clips under light tension, as shown in Figure 8.8.4.3.

8.8.5 Procedure.

8.8.5.1 A balance shall be used to determine the weight of each specimen to the nearest 0.1 g (0.04 oz) before and after testing.

8.8.5.2 The burner shall be ignited, and the test flame shall be adjusted to a height of 75 mm (3 in.) with the gas on/off valve fully open and the air supply completely and permanently off, so that the flame height is closely controlled. The 75 mm (3 in.) height shall be obtained by adjusting the orifice in the bottom of the burner so that the top of the flame is level with the marked flame height indicator.




FIGURE 8.8.4.3 Specimen Support Assembly.

8.8.5.3 With the specimen mounted in the support assembly, the burner shall be moved such that the middle of the folded corner contacts the flame, as shown in Figure 8.8.4.3.

8.8.5.4 The burner flame shall be applied to the specimen for 12 seconds. After 12 seconds, the burner shall be removed.

8.8.5.5 The afterflame time shall be measured as the time, in seconds, to the nearest 0.2 second, that the specimen continues to flame after the burner is removed from the flame.

8.8.5.6 Each layer of the specimen shall be examined for melting or dripping.

8.8.5.7 Each tested sample shall be conditioned a second time as specified in 8.1.2 and then weighed to the nearest 0.1 g (0.04 oz).

8.8.5.8 The specimen shall be further examined for char length by measuring the length of the tear through the center of the charred area as specified in 8.8.5.8.1 through 8.8.5.8.4.

8.8.5.8.1 The specimen shall be folded lengthwise and creased, by hand, along a line through the highest peak of the charred area.

8.8.5.8.2 A hook shall be inserted in the specimen or through a hole 6 mm ($\frac{1}{4}$ in.) in diameter or less punched out for the hook at one side of the charred area, 6 mm ($\frac{1}{4}$ in.) from the adjacent outside edge at the point where the specimen contacted the steel rod, and 6 mm ($\frac{1}{4}$ in.) away from the point where the specimen contacted the steel rod in the 100 mm (4 in.) long direction, as shown in Figure 8.8.5.8.2.

8.8.5.8.3 A weight of sufficient size such that the weight and hook together equal the total tearing load required in Table 8.8.5.8.3 shall be attached to the hook.

8.8.5.8.3.1 The specific load for determining char length applicable to the weight of the composite specimen shall be as listed in Table 8.8.5.8.3.

8.8.5.8.4 A tearing force shall be applied gently to the specimen by grasping the side of the material at the edge of the char opposite from the load, as shown in Figure 8.8.5.8.2, and raising the specimen and weight upward to clear the supporting surface.

8.8.5.8.4.1 The ends of the tear shall be marked off on the edge.

8.8.5.8.4.2 The char length measurement shall be made along the undamaged edge.

8.8.6 Report.

8.8.6.1 The afterflame time and char length shall be recorded and reported for each specimen.

8.8.6.2 The average afterflame time and char length shall be calculated, recorded, and reported.

8.8.6.3 The afterflame time shall be recorded and reported to the nearest 0.2 second, and the char length shall be recorded and reported to the nearest 2.5 mm ($\frac{1}{16}$ in.).

8.8.6.4 Observations of melting or dripping for each specimen shall be recorded and reported.




FIGURE 8.8.5.8.2 Sample Preparation for Measuring Char Length.

Table 8.8.5.8.3 Tearing Weights for Determining Charred Lengths

Specified Weight of Material Before Any Fire-Retardant Treatment or Coating		Total Tearing Weight for Determining Charred Length	
g/m ²	oz/yd ²	kg	lb
68–203	2.0–6.0	0.1	0.25
>203–508	>6.0–15.0	0.2	0.5
>508–780	>15.0–23.0	0.3	0.75
>780	>23.0	0.45	1.0

8.8.6.5 The percent consumed shall be calculated using the following formula:

$$\text{Percent Consumed} = \left[\frac{(W - R)}{W} \right] \times 100 \quad [8.8.6.5]$$

where:

W = original preconditioned weight

R = conditioned weight 24 hours after testing

8.8.6.5.1 The percent consumed shall be recorded and reported for each specimen to the nearest 0.1 percent. The average percent consumed shall be calculated, recorded, and reported to the nearest 0.1 percent.

8.8.7 Interpretation. Pass or fail performance shall be based on any observed melting or dripping, the average afterflame time, the average char length, and the average percent consumed.

8.8.8 Specific Requirements for Testing Small Materials.

8.8.8.1 No fewer than three specimens attached to the glove exterior layer shall be tested.

8.8.8.2 The specimens shall be attached to the glove exterior layer such that the exposure of the items is centered on the support rod with equivalent area extending vertically and horizontally along the sample.

8.8.8.3 Testing shall be performed as described in 8.8.4 through 8.8.6, except char length and percent consumed shall not be measured.

Annex A Explanatory Material

Annex A is not a part of the requirements of this NFPA document but is included for informational purposes only. This annex contains explanatory material, numbered to correspond with the applicable text paragraphs.

A.1.2.1 Users are cautioned that non-flame resistant clothing can contribute to the severity of burn injuries through its ignition and continued burning after exposure to fire.

Short-duration thermal exposures can arise from multiple fire types in industrial environments. These include, but are not limited to vapor cloud fires, jet flames, liquid fires (pool fires or running liquid fires), solids fires (fires of solid materials or dust fires), or warehouse fires.

A.1.2.2 The testing requirements in Chapter 8 of this standard are not intended to establish the limitations of the working environment for personnel involved in situations that might be exposed to chemical fires, but are intended to establish material performance.

Users should be advised that if unusual conditions prevail, or if there are signs of abuse or mutilation of the protective garment, or if modifications or replacements are made or accessories are added without authorization of the protective garment manufacturer, the margin of protection might be reduced.

Users should be advised that the protective properties in new protective garments, as required by this standard, can change as the product is worn and ages.

A.1.2.3 This standard is not designed to be utilized as a purchase specification. It is prepared, as far as practical, with regard to required performance, avoiding restriction of design wherever possible. Purchasers should specify departmental requirements for such items as color, markings, closures, pockets, and trim patterns. Tests specified in this standard should not be deemed as defining or establishing performance levels for protection from all fire environments.

A.1.3.2 Organizations responsible for firefighting applications should use protective clothing and equipment specifically designed for those activities. Applicable standards include NFPA 1971 and NFPA 1977.

Organizations responsible for hazardous materials emergencies should use protective clothing and equipment specifically designed for those activities. Applicable standards include NFPA 1991 and NFPA 1992.

Organizations responsible for emergency medical operations should use protective clothing and equipment specifically designed for those activities. The applicable standard is NFPA 1999.

A.3.2.1 Approved. The National Fire Protection Association does not approve, inspect, or certify any installations, procedures, equipment, or materials nor does it approve or evaluate testing laboratories. In determining the acceptability of installations or procedures, equipment, or materials, the "authority having jurisdiction" may base acceptance on compliance with NFPA or other appropriate standards. In the absence of such standards, said authority may require evidence of proper installation, procedure, or use. The "authority having jurisdiction" may also refer to the listings or labeling practices of an organization that is concerned with product evaluations and is thus in a position to determine compliance with appropriate standards for the current production of listed items.

A.3.2.2 Authority Having Jurisdiction (AHJ). The phrase "authority having jurisdiction," or its acronym AHJ, is used in NFPA standards in a broad manner because jurisdictions and approval agencies vary, as do their responsibilities. Where public safety is primary, the authority having jurisdiction may be a federal, state, local, or other regional department or individual such as a fire chief; fire marshal; chief of a fire prevention bureau, labor department, or health department; building official; electrical inspector; or others having statutory authority. For insurance purposes, an insurance inspection department, rating bureau, or other insurance company representative may be the authority having jurisdiction. In many circumstances, the property owner or his or her designated agent assumes the role of the authority having jurisdiction; at government installations, the commanding officer or departmental official may be the authority having jurisdiction.

A.3.2.4 Listed. The means for identifying listed equipment may vary for each organization concerned with product evaluation; some organizations do not recognize equipment as listed unless it is also labeled. The authority having jurisdiction should utilize the system employed by the listing organization to identify a listed product.

A.3.3.3 Barrier Face Covering. Barrier face coverings are not shrouds/hoods/balaclavas because they are not designed to provide primary thermal protection to the wearer's head or neck, or both. Barrier face coverings provide primary thermal protection to the nose and mouth that is consistent with the

performance levels that are applied for shrouds/hoods/balaclavas for flame resistance and heat resistance, but not thermal insulation.

Barrier face coverings are separately assessed for their functional design and performance as specified in ASTM F3502, *Standard Specification for Barrier Face Coverings*. In that standard, barrier face coverings are assessed for airflow resistance; filtration performance using sub-micron particulate filtration efficiency testing; and the degree of face coverage per a leakage assessment using a product design analysis that can be supplemented by quantitative testing using test subjects. Other specific design, performance, classification, labeling, and user documentation requirements are also addressed in ASTM F3502.

Barrier face coverings are sometimes referred to as “masks.” They are distinct from surgical/medical/isolation masks or NIOSH-approved respirators that are also referred to as masks, since those products are subject to different requirements and qualifications that are not within the scope of ASTM F3502.

A.3.3.8 Cold Weather Insulation Material. Examples of insulation materials include textile batting(s) alone or batting(s) that are attached to a face cloth. For example, an insulation material consisting of two layers is considered nonseparable by the attachment that combines the two layers. The insulation material might or might not have a face cloth. Cold weather insulation materials generally are provided within the garment such that their area of coverage coincides with the majority of garment area covering the wearer’s body.

Cold weather insulation material as defined in this standard does not preclude the use of intermediate layers for additional protection against thermal hazards.

Cold weather insulation material is not an interlining (*see 3.3.25, Interlining*).

A.3.3.12 Emblem(s). Emblems can include transfer films that are thin films applied to fabric via the application of heat.

A.3.3.13 Fabric. Where a garment is constructed of multiple, nonseparable layers, such as an outer layer and cold weather insulation material, *fabric* is intended to mean the composite of those layers for the purpose of testing.

A.3.3.14 Fire. Fire is the result of combustion, or the chemical process of rapid oxidation (burning) that requires an ignition source, a flammable substance or fuel, and oxygen (usually from air). In an industrial environment, different fires can result from a variety of events. “Jet” fires typically arise from line breaks or ruptures of pressurized flammable materials. These fires can create directed “jets” or “flares,” which can project flames in any direction for considerable distances, depending on the characteristics of the source, and burn until the fuel is exhausted or the break is isolated. A pool or running pool fire arises from the ignition of spills and leaks of flammable liquids. The size and intensity depends on the amount of material involved and typically extends upward from the surface of the pool. These fires also continue until the fuel is exhausted, and the source of the leak isolated. A flash or vapor cloud fire arises from the release or presence of a flammable gas or combustible, finely divided particles (e.g., coal dust or grain) that contain a concentration above the lower explosive limit of the chemical. Flash fire characteristics depend on the size of the gas or vapor cloud and local conditions. When ignited, the flame front can expand outward in the form of a fire-

ball or be driven by external convection (wind). The effect of the fireball or flame front’s energy with respect to radiant heat significantly enlarges the hazard areas around the released gas.

A.3.3.15 Flame Resistance. Flame resistance can be an inherent property of a material, or it can be imparted by specific treatment.

A.3.3.19.2 Single-Use Garment. What constitutes a “use” will be defined by the garment manufacturer. A single use could include unpacking, or one donning, or one wearing. In the absence of any manufacturer’s specific information, one “use” should be considered any one-time wearing of the garment.

A.3.3.25 Interlining. The outer and inner layers are compliant to the fabric requirements of this standard. Examples of an interlining are a fabric layer used to stiffen the waistband in a pair of pants or a facing fabric used inside the closure flap of a overall. Interlining materials do not contact the wearer’s skin or underclothing.

A.3.3.29 Product. Barrier face coverings are intentionally omitted from the definition of product because they are exempt from many requirements that are imposed on products throughout this standard.

A.3.3.30 Product Label. The product label is not the label, symbol, or identifying mark of the certification organization; however, the label, symbol, or identifying mark of the certification organization can be attached to, or can be part of, the product label.

A.3.3.36 Short-Duration Thermal Exposure from Fire. This standard establishes minimum requirements for clothing that provides limited protection from short-duration thermal exposure from fire with the aim of limiting potential injury to persons egressing from or encountering accidental hazardous exposures to fire. See the requirements established in NFPA 2113 for selection, care, and maintenance of these clothing items.

A.3.3.37 Shroud/Hood/Balaclava. Shrouds/hoods/balaclavas that incorporate mouth and nose coverage that is intended to provide primary thermal protection are still to be considered as shrouds/hoods/balaclavas and not barrier face coverings.

A.4.1.3.2 Testing that is conducted at a technically competent, independent, ISO 17025–accredited lab, free from influence or control by a product manufacturer or vendor, is a reliable approach for material selection and certification.

A.4.1.5 NFPA occasionally receives complaints that certain items of fire and emergency services protective clothing or protective equipment might be carrying labels falsely identifying them as compliant with an NFPA standard. The requirement for placing the certification organization’s mark on or next to the product label helps to ensure that the purchaser can readily determine compliance of the respective product through independent third-party certification.

A.4.2.1 The certification organization should have sufficient breadth of interest and activity so that the loss or award of a specific business contract would not be a determining factor in the financial well-being of the agency.

A.4.2.5 The contractual provisions covering a certification program should contain clauses advising the manufacturer that if requirements change, the product should be brought into compliance with the new requirements by a stated effective

date through a compliance review program involving all currently listed products.

Without the clauses, certifiers would not be able to move quickly to protect their name, marks, or reputation. A product safety certification program would be deficient without these contractual provisions and the administrative means to back them up.

A.4.2.9 Investigative procedures are important elements of an effective and meaningful product safety certification program. A preliminary review should be carried out on products submitted to the agency before any major testing is undertaken.

Good practice should be followed regarding the use of laboratory manuals, form data sheets, documented calibration and calibration routines, performance verification, proficiency testing, and staff qualification training programs.

A.4.2.11 Such inspections should include, in most instances, witnessing of production tests. With certain products, the certification organization inspectors should select samples from the production line and submit them to the main laboratory for countercheck testing. With other products, it might be desirable to purchase samples in the open market for test purposes.

A.4.2.15 For further information and guidance on recall programs, see Subpart C of 21 CFR 7, "Recalls (Including Product Corrections) — Guidance on Policy, Procedures, and Industry Responsibilities."

A.4.4.1.3 ISO 9000, *Quality management systems — Fundamentals and vocabulary*, defines quality terms and concepts. It gives an overview of the content and use of the entire ISO 9000 series. A useful cross-reference to the series' quality system elements is found in Annex A of ISO 9000.

ISO 9001, *Quality management systems — Requirements*, is used when the quality system to be assessed covers several stages of one firm's processes. It prescribes quality system requirements for design, development, production, installation, and servicing.

A.5.1.1 Purchasers might wish to include a requirement in the purchase specifications for an additional label that includes certain information such as the date of manufacture, manufacturer's name, and protective clothing item identification number to be located in a protected location on the protective clothing item in order to reduce the chance of label degradation and as a backup source of information to aid in protective clothing item tracking or during an investigation.

A.5.1.4 See A.4.1.5.

A.5.1.9.1 The reduced minimum label information for flame-resistant barrier face coverings is intended to minimize the size of the label relative to the inherently small size of the item.

Additional label information is permitted if requested by the end-user.

A.5.2.1 The required information can be provided either with the use of a suitable electronic link or with accompanying printed literature packaged with each clothing item.

A.5.2.2 The selection of protective clothing size relates directly to the clothing items' ability to function properly. In occupations such as the petrochemical industry, proper fit and function relate directly to the wearer's ability to perform assigned jobs. Issues of proper fit are directly associated with

the risk of injury. Protective clothing that restricts movement will result in lost efficiency and can promote injury and illness. Proper sizing is a factor in the ability of a person to perform tasks that often involve life or death situations. Protective clothing must fit well to function properly when additional safety equipment or other garments are worn. In addition, the selection of flame-resistant clothing item size has a direct impact on maintaining appropriate protection in areas where the flame-resistant clothing item has an interface with safety equipment or other protective clothing items. ASTM F1731, *Standard Practice for Body Measurements and Sizing of Fire and Rescue Services Uniforms and Other Thermal Hazard Protective Clothing*, might be found useful when selecting protective clothing for technical operations. ASTM F1731 primarily addresses processes for sizing flame-resistant clothing item; however, the techniques described are useful in the selection of protective clothing addressed in this standard. The required information can be provided either with the use of a suitable electronic link or with accompanying printed literature packaged with each clothing item.

A.6.2.1 Removable liners are permitted to be worn separately if the liner material(s) independently meets the appropriate fabric requirements in Chapter 7 including 7.1.1 for heat transfer performance and 7.1.5 for overall flash fire performance. If the liner contains cold weather insulation materials that are not evaluated to 7.1.1 and 7.1.5 and do not pass the thermal shrinkage resistance requirement in 7.1.3, then the manufacturer must label the liner as specified in 5.1.13 and provide a design that does not allow separate wearing of the liner without the outer layer. This can be demonstrated by the absence of a means of closure for the closure area of shirts, pants, and coveralls.

A.7.1.2.1 If non-flame-resistant emblems are attached to the exterior of a garment, the maximum number should be five with no individual emblem covering an area greater than 103 cm² (16.0 in.²) or total area from all these emblems covering an area greater than 258 cm² (40 in.²).

A.7.1.5.2 Paragraph 7.1.5.2 does not apply to rainwear.

A.7.3 Hook and pile fasteners are considered fabric-based components.

A.8.1.3 Tergitol 15.S.9 is available from Union Carbide. Sodium metasilicate is available from Tilly Chemical Co. under the trade name Metso 2048 beads, anhydrous sodium metasilicate. Sodium tripolyphosphate is available from Tilly Chemical Co. under the trade name Amoto. Sodium silicofluoride is available from UNX Chemical Co. under the trade name Sourcide. Materials from other sources that are of equivalent chemical composition and concentration can be used in place of the laundry chemicals listed herein.

One example of a suitable industrial laundry machine is a Milnor Model 30015C6M-AAC. Equivalents can be used.

One example of a suitable industrial tumble dryer is a Huebsch Originator, Model 37CSH. Equivalents can be used.

A.8.1.3(2) The two chemical-free cycles are intended to remove any residuals from the test specimens.

A.8.3.11.1 This testing is intended to demonstrate the flame resistance of specific emblem technology. Testing of representative emblems should be applied to demonstrate the efficacy of specific emblem technology.

A.8.5.6.3.3 Single threads across the opening or hole do not reduce the size of the hole for the purposes of this standard. Figure A.8.5.6.3.3 is an example of taking the measurements of a breakopen area.

A.8.5.6.3.3.1 Though physical contact is permitted, care must be taken to ensure that further degradation of the garment or further breakopen does not occur.




FIGURE A.8.5.6.3.3 Breakopen Area Measurement Example.

Annex B Properties for Evaluating Flame-Resistant Garments, Shrouds/Hoods/Balaclavas, and Gloves

This annex is not a part of the requirements of this NFPA document but is included for informational purposes only.

B.1 Test Properties and Methods. Table B.1 provides a description of the test properties and methods used for evaluating flame-resistant garments, shrouds/hoods/balaclavas, and gloves. A number of additional properties can be used in the evaluation of flame-resistant garments, shrouds/hoods/balaclavas, and gloves that are not required as part of this standard. Table B.1 also lists these additional properties, recommended test methods, and their suggested application.



Table B.1 Performance Properties and Additional Evaluation Properties for Flame-Resistant Garments, Shrouds/Hoods/Balaclavas, and Gloves

Property (Section No.)	Test Method Cited	Description of Test Method	Application of Test Method
Mandatory Tests			
Heat transfer performance (HTP) (7.1.1)	Method appears in Section 8.2.	A 150 mm (6 in.) square fabric specimen is placed on a specimen holder that suspends the specimen horizontally over two Meker burners and a radiant panel. The heat and flame source is adjusted to provide an exposure heat flux of 84 kW/m ² (2.0 cal/cm ² · sec). A weighted sensor containing a copper calorimeter is placed on top of the specimen and measures the heat transfer through the specimen. A water-cooled shutter between the specimen and heat source is withdrawn to begin the exposure. The test measures the amount of time with continuous heating for heat breakthrough resistance (using an arbitrary criterion of heat through the specimen to cause a second-degree burn). This time is multiplied by the exposure heat flux to provide an HTP rating. HTP ratings are measured with the sensor both in “contact” with the specimen and “spaced” 6 mm (¼ in.) away from the specimen. Note that this test method does not result in a burn injury prediction. The heat remaining in a test sample is not accounted for, which would otherwise contribute to a predicted skin burn injury.	This test is a measure of the unsteady state heat transfer properties of garment, shroud/hood/balaclava, and glove materials. The HTP test uses an exposure heat flux that is representative of a JP4 (jet fuel) pool fire environment. NFPA 2112 requires that specimens have an HTP rating of 1 2.6 J/cm ² (3.0 cal/cm ²) or more when measured in “contact,” simulating direct contact with the skin, and 25 J/cm ² (6.0 cal/cm ²) or more when measured “spaced,” simulating an air gap between the skin and the garment material. Higher HTP ratings indicate better unsteady state heat transfer performance for this test but do not correlate to improved predicted skin burn injury performance.
Flame resistance (7.1.2)	ASTM D6413/D6413M; washing and drying per commercial laundering procedure or dry cleaning (100 cycles) (Section 8.3)	A 75 mm × 305 mm (3 in. × 12 in.) fabric specimen is placed in a holder that is suspended vertically over a 38 mm (1½ in.) high methane-fueled flame. The specimen is placed 19 mm (¾ in.) into the flame for 12 seconds. After exposure to the flame, the amount of time during which the specimen continues to burn (after-flame) is recorded. The length of the burn or char length is then measured by attaching a weight to the specimen and measuring the length of the tear along the burn line. Observations are recorded if any melting and dripping are observed. Samples are tested in this manner both before and after 100 wash/dry cycles or 100 dry cleaning cycles.	This test is used to determine how easily fabrics ignite and how easily they continue to burn once ignited. In order to pass NFPA 2112, materials cannot have an average after-flame time greater than 2 seconds, a char length greater than 102 mm (4 in.), or any melting with dripping.

(continues)

Table B.1 *Continued*

Property (Section No.)	Test Method Cited	Description of Test Method	Application of Test Method
Thermal shrinkage resistance (7.1.3)	Method appears in Section 8.4; washing and drying per commercial laundering procedure or dry cleaning (3 cycles)	A 381 mm (15 in.) square fabric specimen is marked for width and length dimensions and is then suspended in a forced air-circulating oven at 260°C (500°F). Following a 5-minute exposure, the specimen dimensions are remeasured and then compared against the original measurements to determine the amount of shrinkage. The specimen is examined for evidence of melting, dripping, separation, or ignition. Specimens that demonstrate such behavior fail the test.	A fabric's resistance to shrinkage when exposed to heat is considered important in minimizing the effects of a short-duration thermal exposure from fire. NFPA 2112 permits shrinkage in this laboratory-based test of 10 percent or less. Lower reported shrinkage indicates fabric that is more resistant to thermal shrinkage.
Heat resistance (7.1.4/Section 7.3)	Method appears in Section 8.4; washing and drying per commercial laundering procedure or dry cleaning (3 cycles)	The exposure used for thermal shrinkage is also used for measuring heat resistance. Fabrics or garment components not required to meet thermal shrinkage requirements can be 152 mm (6 in.) square specimens. Following a 5-minute exposure, the specimen is examined for evidence of melting and dripping, separation, or ignition. Specimens that demonstrate such behavior fail the test. The test is also applied to hardware items.	This test measures how garment, shroud/hood/balaclava, and glove fabrics and components react to the high heat that could occur during a short-duration thermal exposure from fire. The purpose of the test is to prevent materials or components that will easily ignite, melt, and drip, or separate during exposure to high heat from being used in garments, shrouds/hoods/balaclavas, and gloves.
Manikin testing (7.1.5)	ASTM F1930; washing and drying per commercial laundering procedure or dry cleaning (1 cycle) (Section 8.5)	The fabric is made into a standardized overall design and placed on an instrumented manikin that is dressed in cotton underwear. The manikin is subjected to an overall flame and heat exposure averaging 84 kW/m ² (2.0 cal/cm ² · sec) for 3 seconds. Sensors embedded in the manikin's skin predict whether a second- or third-degree burn will occur at that specific location. A computer program determines the percentage of the body that would sustain second- or third-degree burns.	This test provides an overall evaluation of how the fabric performs in a standardized overall design. NFPA 2112 requires a body burn prediction of 50 percent or less of the surface area covered by sensors (hands and feet are excluded). Lower percent body burn predictions indicate greater protection provided by the fabric.
Thread melting resistance (Section 7.2)	FTMS 191A, 1534 (Section 8.6)	A small segment of thread used in the stitching of flame-resistant garments, shrouds/hoods/balaclavas, or gloves is placed in a flask containing an organic solvent and heated. (The solvent extracts substances that would interfere with the test.) Next, the extracted thread segment is put in a device that slowly heats the thread. The temperature at which the thread begins to melt is the melting temperature.	Thread used in flame-resistant garments, shrouds/hoods/balaclavas, and gloves must withstand temperatures of up to 260°C (500°F). If the melting temperature is less than 260°C (500°F), the thread fails the test. The temperature, 260°C (500°F), is consistent with the heat resistance test.
Label legibility (Section 7.4)	Method appears in Section 8.7; washing and drying per commercial laundering procedure or dry cleaning (100 cycles)	Sample labels containing the required product information are subjected to 100 wash/dry or dry cleaning cycles and then examined for legibility.	This requirement checks for label durability. Following this test, the labels must remain legible from a distance of at least 305 mm (12 in.).

(continues)

Table B.1 *Continued*

Property (Section No.)	Test Method Cited	Description of Test Method	Application of Test Method
Other Property Evaluations			
Fabric weight	ASTM D3776/D3776M	A known, specific area of fabric is weighed using a laboratory balance. The measured fabric weight is divided by the area of the fabric. This yields a fabric weight in ounces per square yard.	Fabric weights are commonly used to reference materials.
Tensile strength (grab method)	ASTM D5034	In this test, a 102 mm × 204 mm (4 in. × 8 in.) fabric specimen is placed between the two grips of a tensile testing machine and pulled in the direction of the specimen's long axis until it breaks. The force measured at the site of the break is reported as the tensile strength. Tensile strength is reported for both the warp (machine) and fill (cross-machine) directions of the fabric.	Tensile strength is a measurement that describes the ease with which a woven material can be pulled apart. Higher tensile strengths indicate greater fabric strength.
Tear strength (Elmendorf method)	ASTM D1424	In this test, a notched 102 mm × 204 mm (4 in. × 8 in.) material specimen is placed into a test device. The test device uses a pendulum that is allowed to fall by its own weight. The force of the falling pendulum tears the material beyond the notch. This test measures the force in pounds that is required to continue a tear in the notched test specimen. Tear resistance is reported for both the warp (machine) and fill (cross-machine) directions of the fabric.	Tear resistance is a measurement of the ease with which a woven fabric can be torn apart. Higher tear strengths indicate fabrics with greater resistance to tearing.
Material burst strength	ASTM D3787	This test measures the force required to burst a knit or stretch woven fabric. A material specimen is clamped over a diaphragm that is inflated until the specimen bursts. The pressure at which the fabric bursts is the burst strength.	Burst strength is a measure of how easily a knit fabric can be penetrated by a hard round object. Higher burst strength indicates fabrics that are more resistant to bursting.
Laundering shrinkage	AATCC TM135; machine cycle 3; wash temp. IV; and drying procedure Aiii (number of cycles to be specified)	A fabric specimen, on which dimensions are marked and measured in both its width and length, is subjected to a specified number of separate wash/dry cycles under controlled conditions. Following the washing and drying, the dimensions of the material sample are compared to its original dimensions to determine the amount of shrinkage. Shrinkage is reported in both the warp (machine) and fill (cross-machine) directions of the fabric.	Laundering shrinkage is a measure of the percentage a fabric shrinks after laundering. Shrinkage measured for a fabric is not necessarily representative of shrinkage measured for a garment.
Laundering colorfastness	AATCC TM61; color change procedure	A fabric sample is subjected to controlled washing and drying conditions. Following exposure, the color of the material sample is compared to a color scale chart that indicates the degree of a color change. Color scale ratings range from Grade 1 (change in color) to Grade 5 (negligible or no change) in 0.5 increments.	Laundering colorfastness assesses the amount of color change, or fading, that occurs in the fabric following exposure to washing and drying. Fabrics with high color scale ratings are more resistant to color changes in laundering.

(continues)

Table B.1 *Continued*

Property (Section No.)	Test Method Cited	Description of Test Method	Application of Test Method
Dry cleaning colorfastness	AATCC TM132	A fabric sample is subjected to controlled dry cleaning conditions. Following exposure, the color of the material sample is compared to a color scale chart that indicates the degree of a color change. Color scale ratings range from Grade 1 (change in color) to Grade 5 (negligible or no change) in 0.5 increments.	Dry cleaning colorfastness assesses the amount of color change, or fading, that occurs in the fabric following exposure to dry cleaning solvents. Fabrics with high color scale ratings are more resistant to color changes in dry cleaning.
Crocking colorfastness	AATCC TM8	In this test method, a fabric sample is placed in a device against a white transfer cloth. The device rubs the fabric against the transfer cloth. The amount of color that is transferred to the white transfer cloth is assessed by a rating scale of Grade 1 to 5 in 0.5 increments (similar to laundering colorfastness).	Crocking colorfastness is a measure of the amount of color or dye that is transferred from the fabric by rubbing or abrasion. Fabrics with high color scale ratings are more resistant to loss of color through rubbing from wearing.
Light colorfastness, continuous xenon-arc lamp exposure	AATCC TM 16.3, Option e	A fabric specimen is placed in a weatherometer using a water-cooled xenon-arc lamp, which simulates intense exposure to sunlight and humidity. The exposure test is conducted for a total of two weeks. Following the exposure, the fabric is compared to a color scale chart that indicates the degree of color change. Color scale ratings range from Grade 1 to 5 in 0.5 increments (similar to laundering colorfastness).	Light colorfastness is a measure of the amount of color loss in a fabric due to extended exposure to light. Fabrics with high color scale ratings are more resistant to fading when exposed to outdoor light.
Seam efficiency	ASTM D1683/D1683M	The strength of a seam is measured in the same way as fabric tensile strength. In this test, a garment seam specimen is placed between two grips in a tensile testing machine and pulled in a direction perpendicular to the seam line until it breaks. The force to break the seam can be compared to the force to break the fabric by itself. The location of the break in the specimen can also be reported.	Seam efficiency compares the strength of a seam to the fabric that it joins. Higher seam strength indicates stronger seams; however, seams that break in the fabric, as opposed to at the stitching or seam area, are stronger than the fabric itself.

Annex C Informational References

C.1 Referenced Publications. The documents or portions thereof listed in this annex are referenced within the informational sections of this standard and are not part of the requirements of this document unless also listed in Chapter 2 for other reasons.

C.1.1 NFPA Publications. National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 1971, *Standard on Protective Ensembles for Structural Fire Fighting and Proximity Fire Fighting*, 2018 edition.

NFPA 1977, *Standard on Protective Clothing and Equipment for Wildland Fire Fighting*, 2022 edition.

NFPA 1991, *Standard on Vapor-Protective Ensembles for Hazardous Materials Emergencies and CBRN Terrorism Incidents*, 2016 edition.

NFPA 1992, *Standard on Liquid Splash-Protective Ensembles and Clothing for Hazardous Materials Emergencies*, 2018 edition.

NFPA 1999, *Standard on Protective Clothing and Ensembles for Emergency Medical Operations*, 2018 edition.

NFPA 2113, *Standard on Selection, Care, Use, and Maintenance of Flame-Resistant Garments for Protection of Industrial Personnel Against Short-Duration Thermal Exposures from Fire*, 2020 edition.

C.1.2 Other Publications.

C.1.2.1 AATCC Publications. American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

AATCC TM8, *Colorfastness to Crocking: Crockmeter Method*, 2016.

AATCC TM16.3, *Colorfastness to Light: Xenon-Arc*, 2020.

AATCC TM61, *Colorfastness to Laundering: Accelerated*, 2013e2.

AATCC TM132, *Colorfastness to Drycleaning*, 2013e3.

AATCC TM135, *Dimensional Changes of Fabrics After Home Laundering*, 2018.

C.1.2.2 ASTM Publications. ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959.

ASTM D1424, *Standard Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus*, 2009, reapproved 2019.

ASTM D1683/D1683M, *Standard Test Method for Failure in Sewn Seams of Woven Fabrics*, 2017, reapproved 2018.

ASTM D3776/D3776M, *Standard Test Methods for Mass Per Unit Area (Weight) of Fabric*, 2020.

ASTM D3787, *Standard Test Method for Bursting Strength of Textiles — Constant-Rate-of-Traverse (CRT) Ball Burst Test*, 2016, reapproved 2020.

ASTM D5034, *Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)*, 2021.

ASTM D6413/D6413M, *Standard Test Method for Flame Resistance of Textiles (Vertical Test)*, 2015.

ASTM F1731, *Standard Practice for Body Measurements and Sizing of Fire and Rescue Services Uniforms and Other Thermal Hazard Protective Clothing*, 2021.

ASTM F1930, *Standard Test Method for Evaluation of Flame Resistant Clothing for Protection Against Fire Simulations Using an Instrumented Manikin*, 2018.

ASTM F3502, *Standard Specification for Barrier Face Coverings*, 2021.

C.1.2.3 GSA Publications. U.S. General Services Administration, 1800 F Street, NW, Washington, DC 20006.

Method 1534, "Melting Point of Synthetic Fibers," Federal Test Method Standard 191A, *Textile Test Methods*, July 20, 1978.

C.1.2.4 ISO Publications. International Organization for Standardization, ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland.

ISO 9000, *Quality management systems — Fundamentals and vocabulary*, 2015.

ISO 9001, *Quality management systems — Requirements*, 2015.

C.1.2.5 U.S. Government Publications. U.S. Government Publishing Office, 732 North Capitol Street, NW, Washington, DC 20401.

Title 21, Code of Federal Regulations, Part 7, Subpart C, "Recalls (Including Product Corrections) — Guidance on Policy, Procedures, and Industry Responsibilities."

C.2 Informational References. The following documents or portions thereof are listed here as informational resources only. They are not a part of the requirements of this document.

Stoll, A. M., and M. A. Chianta, "Heat Transfer Through Fabrics as Related to Thermal Injury," *Transactions New York Academy of Sciences*, Vol. 33(7), Nov. 1971, pp. 649–670.

Stoll, A. M., and M. A. Chianta, "Method and Rating System for Evaluations of Thermal Protection," *Aerospace Medicine*, Vol. 40, 1969, pp. 1232–1238.

C.3 References for Extracts in Informational Sections. (Reserved)

Index

Copyright © 2022 National Fire Protection Association. All Rights Reserved.

The copyright in this index is separate and distinct from the copyright in the document that it indexes. The licensing provisions set forth for the document are not applicable to this index. This index may not be reproduced in whole or in part by any means without the express written permission of NFPA.

- A-**
- Accreditation/Accredited**
 Definition, 3.3.1
- Administration, Chap. 1**
 Application, 1.3
 Equivalency, 1.5
 Purpose, 1.2
 Retroactivity, 1.4
 Scope, 1.1
 Units, 1.6
- Agents**
 Biological Agents
 Definition, 3.3.2.1
 Definition, 3.3.2
 Radiological Agents
 Definition, 3.3.2.2
- Approved**
 Definition, 3.2.1, A.3.2.1
- Authority Having Jurisdiction (AHJ)**
 Definition, 3.2.2, A.3.2.2
- B-**
- Barrier Face Covering**
 Definition, 3.3.3, A.3.3.3
- Body**
 Definition, 3.3.4
 Lower Body
 Definition, 3.3.4.1
 Upper Body
 Definition, 3.3.4.2
- Breakopen**
 Definition, 3.3.5
- C-**
- Certification, Chap. 4**
 Certification Program, 4.2
 General, 4.1
 Inspection and Testing, 4.3
 Product Modifications, 4.3.10
 Recertification, 4.3.9
 Manufacturer's Quality Assurance Program, 4.4
 Calibration Program, 4.4.5
 General, 4.4.1
 Inspection Status, 4.4.6
 Inspection System, 4.4.4
 Instructions, 4.4.2
 Nonconforming Materials, 4.4.7
 Records, 4.4.3
 Third-Party Audit, 4.4.8
- Certification Organization**
 Definition, 3.3.7
- Certification/Certified**
 Definition, 3.3.6
- Cold Weather Insulation Material**
 Definition, 3.3.8, A.3.3.8
- Compliance/Compliant**
 Definition, 3.3.9
- Component(s)**
 Definition, 3.3.10
- D-**
- Definitions, Chap. 3**
- Design Requirements, Chap. 6**
 Barrier Face Coverings, 6.4
 Garments, Shrouds/Hoods/Balaclavas, Gloves, and Barrier Face Coverings, 6.1
 Hardware Finishes, 6.1.1
 Metal Components, 6.1.2
 Slide Fastener Tape Requirements, 6.1.3
 Use of a Liner for Cold Weather Insulation, 6.2
 Venting Materials, 6.3
- Drip**
 Definition, 3.3.11
- E-**
- Emblem(s)**
 Definition, 3.3.12, A.3.3.12
- Explanatory Material, Annex A**
- F-**
- Fabric**
 Definition, 3.3.13, A.3.3.13
 Textile Fabric
 Definition, 3.3.13.1
- Fire**
 Definition, 3.3.14, A.3.3.14
- Flame Resistance**
 Definition, 3.3.15, A.3.3.15
 Inherent Flame Resistance
 Definition, 3.3.15.1
- Flash Fire**
 Definition, 3.3.16
- Follow-Up Program**
 Definition, 3.3.17
- Functional**
 Definition, 3.3.18

	-G-	Test Properties and Methods, B.1
Garments		
Definition, 3.3.19		
Limited-Use Garment		
Definition, 3.3.19.1		
Single-Use Garment		
Definition, 3.3.19.2, A.3.3.19.2		
Glove		
Definition, 3.3.20		
	-H-	
Hardware		
Definition, 3.3.21		
Hazardous Material		
Definition, 3.3.22		
Hazardous Materials Emergencies		
Definition, 3.3.23		
	-I-	
Industrial Personnel		
Definition, 3.3.24		
Informational References, Annex C		
Interlining		
Definition, 3.3.25, A.3.3.25		
	-L-	
Labeled		
Definition, 3.2.3		
Labeling and Information, Chap. 5		
Product Label Requirements, 5.1		
User Information, 5.2		
Lining		
Definition, 3.3.26		
Listed		
Definition, 3.2.4, A.3.2.4		
	-M-	
Melt		
Definition, 3.3.27		
Model		
Definition, 3.3.28		
	-P-	
Performance Requirements, Chap. 7		
Barrier Face Covering Requirements, 7.7		
Garment and Fabric Requirements, 7.1		
Glove Requirements, 7.6		
Hardware Requirement, 7.3, A.7.3		
Label Requirement, 7.4		
Shroud/Hood/Balaclava Requirements, 7.5		
Thread Requirements, 7.2		
Product		
Definition, 3.3.29, A.3.3.29		
Product Label		
Definition, 3.3.30, A.3.3.30		
Properties for Evaluating Flame-Resistant Garments, Shrouds/ Hoods/Balaclavas, and Gloves, Annex B		
		-R-
		Referenced Publications, Chap. 2
		Reflective Striping
		Definition, 3.3.31
		Reinforcement
		Definition, 3.3.32
	-S-	
		Sample
		Definition, 3.3.33
		Seam
		Definition, 3.3.34
		Sewn Seam
		Definition, 3.3.34.1
		Separate
		Definition, 3.3.35
		Shall
		Definition, 3.2.5
		Short-Duration Thermal Exposure from Fire
		Definition, 3.3.36, A.3.3.36
		Should
		Definition, 3.2.6
		Shroud/Hood/Balaclava
		Definition, 3.3.37, A.3.3.37
		Specimen
		Definition, 3.3.38
		Standard
		Definition, 3.2.7
	-T-	
		Test Methods, Chap. 8
		Flame Resistance Test, 8.3
		Apparatus, 8.3.4
		Application, 8.3.1
		Interpretation, 8.3.7
		Procedure, 8.3.5
		Report, 8.3.6
		Sample Preparation, 8.3.3
		Specific Requirements for Testing Cold Weather Insulation Materials, 8.3.13
		Specific Requirements for Testing Knit Textile Materials, 8.3.9
		Specific Requirements for Testing Nonwoven, Coated, or Laminated Textile Materials, 8.3.10
		Specific Requirements for Testing Reflective Striping, 8.3.12
		Specific Requirements for Testing Small Materials and Emblems Other Than Transfer Films, 8.3.11
		Specific Requirements for Testing Transfer Films, 8.3.14
		Specific Requirements for Testing Woven Textile Materials, 8.3.8
		Specimens, 8.3.2
		Heat and Thermal Shrinkage Resistance Test, 8.4
		Apparatus, 8.4.4
		Application, 8.4.1
		Interpretation, 8.4.7
		Procedure, 8.4.5

- Report, 8.4.6
- Sample Preparation, 8.4.3
- Specific Requirements for Testing Cold Weather Insulation Materials, 8.4.11
- Specific Requirements for Testing Emblems, Including Transfer Films, 8.4.13
- Specific Requirements for Testing Flame-Resistant Garments and Shroud/Hood/Balaclava Textile Materials, 8.4.8
- Specific Requirements for Testing Gloves, 8.4.12
- Specific Requirements for Testing Hardware, 8.4.10
- Specific Requirements for Testing Other Flame-Resistant Garments, Shroud/Hood/Balaclava, Barrier Face Coverings, and Materials (Including Reflective Striping), 8.4.9
- Specimens, 8.4.2
- Heat Transfer Performance (HTP) Test, 8.2
- Apparatus, 8.2.4
- Application, 8.2.1
- Interpretation, 8.2.7
- Procedure, 8.2.5
- Report, 8.2.6
- Sample Preparation, 8.2.3
- Specific Requirements for Testing Specimens from Whole Knitted Gloves, 8.2.8
- Specimens, 8.2.2
- Label Print Durability Test, 8.7
- Application, 8.7.1
- Interpretation, 8.7.7
- Procedure, 8.7.5
- Report, 8.7.6
- Sample Preparation, 8.7.4
- Specific Requirements for Testing Glove Labels, 8.7.8
- Specimens, 8.7.3
- Manikin Test, 8.5
- Apparatus, 8.5.5
- Application, 8.5.1
- Interpretation, 8.5.8
- Procedure, 8.5.6
- Procedure, 8.5.6.3
- Report, 8.5.7
- Breakopen, 8.5.7.3
- Sample Preparation, 8.5.3
- Specimens, 8.5.2
- Standard Reference Garments, 8.5.4
- Protective Glove Flame Resistance Test, 8.8
- Apparatus, 8.8.4
- Application, 8.8.1
- Interpretation, 8.8.7
- Procedure, 8.8.5
- Report, 8.8.6
- Sample Preparation, 8.8.3
- Specific Requirements for Testing Small Materials, 8.8.8
- Specimens, 8.8.2
- Sample Preparation Procedures, 8.1
- Application, 8.1.1
- Dry Cleaning Procedure, 8.1.4
- Room Temperature Conditioning Procedure, 8.1.2
- Washing and Drying Procedure, 8.1.3, A.8.1.3
- Thread Heat Resistance Test, 8.6
- Application, 8.6.1
- Interpretation, 8.6.6
- Procedure, 8.6.4
- Report, 8.6.5
- Sample Preparation, 8.6.3
- Specimens, 8.6.2
- Transfer Film**
- Definition, 3.3.39
- Trouser**
- Definition, 3.3.40
- Venting Material**
- Definition, 3.3.41

Sequence of Events for the Standards Development Process

Once the current edition is published, a Standard is opened for Public Input.

Step 1 – Input Stage

- Input accepted from the public or other committees for consideration to develop the First Draft
- Technical Committee holds First Draft Meeting to revise Standard (23 weeks); Technical Committee(s) with Correlating Committee (10 weeks)
- Technical Committee ballots on First Draft (12 weeks); Technical Committee(s) with Correlating Committee (11 weeks)
- Correlating Committee First Draft Meeting (9 weeks)
- Correlating Committee ballots on First Draft (5 weeks)
- First Draft Report posted on the document information page

Step 2 – Comment Stage

- Public Comments accepted on First Draft (10 weeks) following posting of First Draft Report
- If Standard does not receive Public Comments and the Technical Committee chooses not to hold a Second Draft meeting, the Standard becomes a Consent Standard and is sent directly to the Standards Council for issuance (see Step 4) or
- Technical Committee holds Second Draft Meeting (21 weeks); Technical Committee(s) with Correlating Committee (7 weeks)
- Technical Committee ballots on Second Draft (11 weeks); Technical Committee(s) with Correlating Committee (10 weeks)
- Correlating Committee Second Draft Meeting (9 weeks)
- Correlating Committee ballots on Second Draft (8 weeks)
- Second Draft Report posted on the document information page

Step 3 – NFPA Technical Meeting

- Notice of Intent to Make a Motion (NITMAM) accepted (5 weeks) following the posting of Second Draft Report
- NITMAMs are reviewed and valid motions are certified by the Motions Committee for presentation at the NFPA Technical Meeting
- NFPA membership meets each June at the NFPA Technical Meeting to act on Standards with “Certified Amending Motions” (certified NITMAMs)
- Committee(s) vote on any successful amendments to the Technical Committee Reports made by the NFPA membership at the NFPA Technical Meeting

Step 4 – Council Appeals and Issuance of Standard

- Notification of intent to file an appeal to the Standards Council on Technical Meeting action must be filed within 20 days of the NFPA Technical Meeting
- Standards Council decides, based on all evidence, whether to issue the standard or to take other action

Notes:

1. Time periods are approximate; refer to published schedules for actual dates.
2. Annual revision cycle documents with certified amending motions take approximately 101 weeks to complete.
3. Fall revision cycle documents receiving certified amending motions take approximately 141 weeks to complete.

Committee Membership Classifications^{1,2,3,4}

The following classifications apply to Committee members and represent their principal interest in the activity of the Committee.

1. M *Manufacturer*: A representative of a maker or marketer of a product, assembly, or system, or portion thereof, that is affected by the standard.
2. U *User*: A representative of an entity that is subject to the provisions of the standard or that voluntarily uses the standard.
3. IM *Installer/Maintainer*: A representative of an entity that is in the business of installing or maintaining a product, assembly, or system affected by the standard.
4. L *Labor*: A labor representative or employee concerned with safety in the workplace.
5. RT *Applied Research/Testing Laboratory*: A representative of an independent testing laboratory or independent applied research organization that promulgates and/or enforces standards.
6. E *Enforcing Authority*: A representative of an agency or an organization that promulgates and/or enforces standards.
7. I *Insurance*: A representative of an insurance company, broker, agent, bureau, or inspection agency.
8. C *Consumer*: A person who is or represents the ultimate purchaser of a product, system, or service affected by the standard, but who is not included in (2).
9. SE *Special Expert*: A person not representing (1) through (8) and who has special expertise in the scope of the standard or portion thereof.

NOTE 1: “Standard” connotes code, standard, recommended practice, or guide.

NOTE 2: A representative includes an employee.

NOTE 3: While these classifications will be used by the Standards Council to achieve a balance for Technical Committees, the Standards Council may determine that new classifications of member or unique interests need representation in order to foster the best possible Committee deliberations on any project. In this connection, the Standards Council may make such appointments as it deems appropriate in the public interest, such as the classification of “Utilities” in the National Electrical Code Committee.

NOTE 4: Representatives of subsidiaries of any group are generally considered to have the same classification as the parent organization.

Submitting Public Input / Public Comment Through the Online Submission System

Following publication of the current edition of an NFPA standard, the development of the next edition begins and the standard is open for Public Input.

Submit a Public Input

NFPA accepts Public Input on documents through our online submission system at www.nfpa.org. To use the online submission system:

- Choose a document from the List of NFPA codes & standards or filter by Development Stage for “codes accepting public input.”
- Once you are on the document page, select the “Next Edition” tab.
- Choose the link “The next edition of this standard is now open for Public Input.” You will be asked to sign in or create a free online account with NFPA before using this system.
- Follow the online instructions to submit your Public Input (see www.nfpa.org/publicinput for detailed instructions).
- Once a Public Input is saved or submitted in the system, it can be located on the “My Profile” page by selecting the “My Public Inputs/Comments/NITMAMs” section.

Submit a Public Comment

Once the First Draft Report becomes available there is a Public Comment period. Any objections or further related changes to the content of the First Draft must be submitted at the Comment Stage. To submit a Public Comment follow the same steps as previously explained for the submission of Public Input.

Other Resources Available on the Document Information Pages

Header: View document title and scope, access to our codes and standards or NFCSS subscription, and sign up to receive email alerts.

 Current & Prior Editions	Research current and previous edition information.
 Next Edition	Follow the committee’s progress in the processing of a standard in its next revision cycle.
 Technical Committee	View current committee rosters or apply to a committee.
 Ask a Technical Question	For members, officials, and AHJs to submit standards questions to NFPA staff. Our Technical Questions Service provides a convenient way to receive timely and consistent technical assistance when you need to know more about NFPA standards relevant to your work.
 News	Provides links to available articles and research and statistical reports related to our standards.
 Purchase Products & Training	Discover and purchase the latest products and training.
 Related Products	View related publications, training, and other resources available for purchase.

Information on the NFPA Standards Development Process

I. Applicable Regulations. The primary rules governing the processing of NFPA standards (codes, standards, recommended practices, and guides) are the NFPA *Regulations Governing the Development of NFPA Standards (Regs)*. Other applicable rules include NFPA *Bylaws*, NFPA *Technical Meeting Convention Rules*, NFPA *Guide for the Conduct of Participants in the NFPA Standards Development Process*, and the NFPA *Regulations Governing Petitions to the Board of Directors from Decisions of the Standards Council*. Most of these rules and regulations are contained in the *NFPA Standards Directory*. For copies of the *Directory*, contact Codes and Standards Administration at NFPA headquarters; all these documents are also available on the NFPA website at “www.nfpa.org/regs.”

The following is general information on the NFPA process. All participants, however, should refer to the actual rules and regulations for a full understanding of this process and for the criteria that govern participation.

II. Technical Committee Report. The Technical Committee Report is defined as “the Report of the responsible Committee(s), in accordance with the Regulations, in preparation of a new or revised NFPA Standard.” The Technical Committee Report is in two parts and consists of the First Draft Report and the Second Draft Report. (See *Regs* at Section 1.4.)

III. Step 1: First Draft Report. The First Draft Report is defined as “Part one of the Technical Committee Report, which documents the Input Stage.” The First Draft Report consists of the First Draft, Public Input, Committee Input, Committee and Correlating Committee Statements, Correlating Notes, and Ballot Statements. (See *Regs* at 4.2.5.2 and Section 4.3.) Any objection to an action in the First Draft Report must be raised through the filing of an appropriate Comment for consideration in the Second Draft Report or the objection will be considered resolved. [See *Regs* at 4.3.1 (b).]

IV. Step 2: Second Draft Report. The Second Draft Report is defined as “Part two of the Technical Committee Report, which documents the Comment Stage.” The Second Draft Report consists of the Second Draft, Public Comments with corresponding Committee Actions and Committee Statements, Correlating Notes and their respective Committee Statements, Committee Comments, Correlating Revisions, and Ballot Statements. (See *Regs* at 4.2.5.2 and Section 4.4.) The First Draft Report and the Second Draft Report together constitute the Technical Committee Report. Any outstanding objection following the Second Draft Report must be raised through an appropriate Amending Motion at the NFPA Technical Meeting or the objection will be considered resolved. [See *Regs* at 4.4.1 (b).]

V. Step 3a: Action at NFPA Technical Meeting. Following the publication of the Second Draft Report, there is a period during which those wishing to make proper Amending Motions on the Technical Committee Reports must signal their intention by submitting a Notice of Intent to Make a Motion (NITMAM). (See *Regs* at 4.5.2.) Standards that receive notice of proper Amending Motions (Certified Amending Motions) will be presented for action at the annual June NFPA Technical Meeting. At the meeting, the NFPA membership can consider and act on these Certified Amending Motions as well as Follow-up Amending Motions, that is, motions that become necessary as a result of a previous successful Amending Motion. (See 4.5.3.2 through 4.5.3.6 and Table 1, Columns 1-3 of *Regs* for a summary of the available Amending Motions and who may make them.) Any outstanding objection following action at an NFPA Technical Meeting (and any further Technical Committee consideration following successful Amending Motions, see *Regs* at 4.5.3.7 through 4.6.5) must be raised through an appeal to the Standards Council or it will be considered to be resolved.


VI. Step 3b: Documents Forwarded Directly to the Council. Where no NITMAM is received and certified in accordance with the *Technical Meeting Convention Rules*, the standard is forwarded directly to the Standards Council for action on issuance. Objections are deemed to be resolved for these documents. (See *Regs* at 4.5.2.5.)

VII. Step 4a: Council Appeals. Anyone can appeal to the Standards Council concerning procedural or substantive matters related to the development, content, or issuance of any document of the NFPA or on matters within the purview of the authority of the Council, as established by the *Bylaws* and as determined by the Board of Directors. Such appeals must be in written form and filed with the Secretary of the Standards Council (see *Regs* at Section 1.6). Time constraints for filing an appeal must be in accordance with 1.6.2 of the *Regs*. Objections are deemed to be resolved if not pursued at this level.

VIII. Step 4b: Document Issuance. The Standards Council is the issuer of all documents (see Article 8 of *Bylaws*). The Council acts on the issuance of a document presented for action at an NFPA Technical Meeting within 75 days from the date of the recommendation from the NFPA Technical Meeting, unless this period is extended by the Council (see *Regs* at 4.7.2). For documents forwarded directly to the Standards Council, the Council acts on the issuance of the document at its next scheduled meeting, or at such other meeting as the Council may determine (see *Regs* at 4.5.2.5 and 4.7.4).

IX. Petitions to the Board of Directors. The Standards Council has been delegated the responsibility for the administration of the codes and standards development process and the issuance of documents. However, where extraordinary circumstances requiring the intervention of the Board of Directors exist, the Board of Directors may take any action necessary to fulfill its obligations to preserve the integrity of the codes and standards development process and to protect the interests of the NFPA. The rules for petitioning the Board of Directors can be found in the *Regulations Governing Petitions to the Board of Directors from Decisions of the Standards Council* and in Section 1.7 of the *Regs*.

X. For More Information. The program for the NFPA Technical Meeting (as well as the NFPA website as information becomes available) should be consulted for the date on which each report scheduled for consideration at the meeting will be presented. To view the First Draft Report and Second Draft Report as well as information on NFPA rules and for up-to-date information on schedules and deadlines for processing NFPA documents, check the NFPA website (www.nfpa.org/docinfo) or contact NFPA Codes & Standards Administration at (617) 984-7246.



CODES AND STANDARDS GO DIGITAL. AND GO ANYWHERE.

**TRY NFPA LiNK® FREE FOR 14 DAYS
AND GET DIGITAL ACCESS TO
CODES AND STANDARDS.**

Discover NFPA LiNK. It's dynamic digital access to codes and standards, right at your fingertips. Search, share, and find solutions on the job, faster and more efficiently. Now you can get your first two weeks free with a hassle-free trial, at no cost and no credit card required. If NFPA LiNK is right for you, subscriptions start as low as \$9.99/month. Experience the power of NFPA LiNK for yourself.

Learn more and activate your risk-free trial for 14 days free at nfpa.org/LiNK

